



0086

Colas Ltd, Rowfant, Crawley, West Sussex RH10 4NF

Carnsew Quarry

12

0086-CPD-590156

DoP/CQ/A2201

EN 13108-4: 2006

A2201

HRA 50/14 reg/bin 40/60

Intended to be used for Regulating/Binder Course

Target grading passing sieve

Sieve (mm)	Passing (%)
20	100
14	98
10	82
2	44
0.5	22
0.25	15
0.063	5.0

Target binder content (%)	6.4
Minimum temperature (°C)	150
Maximum Temperature (°C)	190