



0086

Colas Ltd, Rowfant, Crawley, West Sussex RH10 4NF

Carnsew Quarry

12

0086-CPD-590156

DoP/CQ/A3404

EN 13108-4: 2006

A3404

HRA 55/10 F surf 40/60 des PSV57

Intended to be used for Surface Course

Target grading passing sieve

Sieve (mm)	Passing (%)
14	100
10	98
6.3	53
2	41
0.5	36
0.25	20
0.063	6.0

Target binder content (%)	5.8
Minimum temperature (°C)	150
Maximum Temperature (°C)	190