



0086

Colas Ltd, Rowfant, Crawley, West Sussex RH10 4NF

Carnsew Quarry

12

0086-CPD-590156

DoP/CQ/A3503

EN 13108-4: 2006

A3503

HRA 55/14 F surf 40/60 des PSV65

Intended to be used for Surface Course

Target grading passing sieve

Sieve (mm)	Passing (%)
20	100
14	98
10	53
2	41
0.5	36
0.25	22
0.063	6.0

Target binder content (%)	5.7
Minimum temperature (°C)	150
Maximum Temperature (°C)	190