



0086

Colas Ltd, Rowfant, Crawley, West Sussex RH10 4NF

Carnsew Quarry

12

0086-CPD-590156

DoP/CQ/A6101

EN 13108-4: 2006

**A6101**

HRA 0/2 F surf 40/60 rec

Intended to be used for Surface Course

Target grading passing sieve

Sieve (mm)	Passing (%)
6.3	100
2	97
0.5	90
0.25	55
0.063	14.0

Target binder content (%)	10.2
Minimum temperature (°C)	150
Maximum Temperature (°C)	190