



0086

Colas Ltd, Rowfant, Crawley, West Sussex RH10 4NF

Carnsew Quarry

12

0086-CPD-590156

DoP/CQ/A6204

EN 13108-4: 2006

A6204

HRA 15/10 F surf 40/60 rec

Intended to be used for Surface Course

Target grading passing sieve

Sieve (mm)	Passing (%)
14	100
10	95
6.3	83
2	79
0.5	71
0.25	42
0.063	12.0

Target binder content (%)	8.8
Minimum temperature (°C)	150
Maximum Temperature (°C)	190