



0086

Colas Ltd, Rowfant, Crawley, West Sussex RH10 4NF

Carnsew Quarry

12

0086-CPD-590156

DoP/CQ/A6303

EN 13108-4: 2006

**A6303**

HRA 30/10 F surf 100/150 rec

Intended to be used for Surface Course

Target grading passing sieve

Sieve (mm)	Passing (%)
14	100
10	95
6.3	74
2	65
0.5	59
0.25	35
0.063	9.0

Target binder content (%)	7.7
Minimum temperature (°C)	130
Maximum Temperature (°C)	170