



0086

Colas Ltd, Rowfant, Crawley, West Sussex RH10 4NF

Carnsew Quarry

12

0086-CPD-590156

DoP/CQ/A9007

EN 13108-4: 2006

**A9007**

HRA 55/14 C surf rec

**Intended to be used for Surface Course**

Target grading passing sieve

Sieve (mm)	Passing (%)
20	100
14	98
10	56
2	40
0.5	18
0.25	13
0.063	6.0

Target binder content (%)	6.1
Minimum temperature (°C)	130
Maximum Temperature (°C)	170