



0086

Colas Ltd, Rowfant, Crawley, West Sussex RH10 4NF

Carnsew Quarry

12

0086-CPD-590156

DoP/CQ/M5212

EN 13108-1: 2006

M5212

AC 32 dense base 100/150 rec

Intended to be used for Base

Target grading passing sieve

Sieve (mm)	Passing (%)
40	100
31.5	99
20	86
6.3	52
2	32
0.25	11
0.063	6.0

Target binder content (%)	4.0
Minimum temperature (°C)	130
Maximum Temperature (°C)	170