



0086

Colas Ltd, Rowfant, Crawley, West Sussex RH10 4NF

Carnsew Quarry

12

0086-CPD-590156

DoP/CQ/M5217

EN 13108-1: 2006

M5217

AC 32 HDM base 40/60 rec

Intended to be used for Base

Target grading passing sieve

| Sieve (mm) | Passing (%) |
|------------|-------------|
| 40 | 100 |
| 31.5 | 99 |
| 20 | 81 |
| 6.3 | 52 |
| 2 | 32 |
| 0.25 | 11 |
| 0.063 | 8.0 |

| | |
|---------------------------|-----|
| Target binder content (%) | 4.0 |
| Minimum temperature (°C) | 150 |
| Maximum Temperature (°C) | 190 |