



0086

Colas Ltd, Rowfant, Crawley, West Sussex RH10 4NF

Carnsew Quarry

12

0086-CPD-590156

DoP/CQ/M6518

EN 13108-1: 2006

M6518

AC 20 dense bin 40/60 rec

Intended to be used for Binder Course

Target grading passing sieve

Sieve (mm)	Passing (%)
31.5	100
20	99
10	62
6.3	47
2	32
0.25	13
0.063	6.0

Target binder content (%)	4.9
Minimum temperature (°C)	150
Maximum Temperature (°C)	190