



0086

Colas Ltd, Rowfant, Crawley, West Sussex RH10 4NF

Carnsew Quarry

12

0086-CPD-590156

DoP/CQ/M7101

EN 13108-1: 2006

M7101

AC 14 open surf 100/150

Intended to be used for Surface Course

Target grading passing sieve

| Sieve (mm) | Passing (%) |
|------------|-------------|
| 20 | 100 |
| 14 | 99 |
| 10 | 65 |
| 6.3 | 34 |
| 2 | 16 |
| 0.063 | 5.0 |

| | |
|---------------------------|-----|
| Target binder content (%) | 5.6 |
| Minimum temperature (°C) | 130 |
| Maximum Temperature (°C) | 170 |