



0086

Colas Ltd, Rowfant, Crawley, West Sussex RH10 4NF

Carnsew Quarry

12

0086-CPD-590156

DoP/CQ/M7102

EN 13108-1: 2006

**M7102**

AC 14 open surf 160/220

Intended to be used for Surface Course

Target grading passing sieve

Sieve (mm)	Passing (%)
20	100
14	99
10	65
6.3	34
2	16
0.063	5.0

Target binder content (%)	5.6
---------------------------	-----

Minimum temperature (°C)	130
--------------------------	-----

Maximum Temperature (°C)	170
--------------------------	-----