



0086

Colas Ltd, Rowfant, Crawley, West Sussex RH10 4NF

Carnsew Quarry

12

0086-CPD-590156

DoP/CQ/M7415

EN 13108-1: 2006

**M7415**

AC 10 close surf 100/150

Intended to be used for Surface Course

Target grading passing sieve

| Sieve (mm) | Passing (%) |
|------------|-------------|
| 14         | 100         |
| 10         | 98          |
| 6.3        | 67          |
| 2          | 28          |
| 1          | 20          |
| 0.063      | 6.0         |

|                           |     |
|---------------------------|-----|
| Target binder content (%) | 5.7 |
| Minimum temperature (°C)  | 130 |
| Maximum Temperature (°C)  | 170 |