



0086

Colas Ltd, Rowfant, Crawley, West Sussex RH10 4NF

Carnsew Quarry

12

0086-CPD-590156

DoP/CQ/M7504

EN 13108-1: 2006

**M7504**

AC 6 dense surf 100/150 Red

Intended to be used for Surface Course

Target grading passing sieve

| Sieve (mm) | Passing (%) |
|------------|-------------|
| 10         | 100         |
| 6.3        | 98          |
| 2          | 47          |
| 1          | 32          |
| 0.25       | 15          |
| 0.063      | 5.0         |

|                           |     |
|---------------------------|-----|
| Target binder content (%) | 7.3 |
| Minimum temperature (°C)  | 130 |
| Maximum Temperature (°C)  | 170 |