



0086

Colas Ltd, Rowfant, Crawley, West Sussex RH10 4NF

Carnsew Quarry

12

0086-CPD-590156

DoP/CQ/M7506

EN 13108-1: 2006

M7506

AC 6 dense surf 160/220

Intended to be used for Surface Course

Target grading passing sieve

Sieve (mm)	Passing (%)
10	100
6.3	98
2	47
1	32
0.25	15
0.063	5.0
Target binder content (%)	7.3
Minimum temperature (°C)	130
Maximum Temperature (°C)	170