



0086

Colas Ltd, Rowfant, Crawley, West Sussex RH10 4NF

Carnsew Quarry

12

0086-CPD-590156

DoP/CQ/M7602

EN 13108-1: 2006

M7602

AC 6 med surf 160/220

Intended to be used for Surface Course

Target grading passing sieve

Sieve (mm)	Passing (%)
10	100
6.3	98
2	33
1	23
0.063	4.0

Target binder content (%)	5.7
Minimum temperature (°C)	130
Maximum Temperature (°C)	170