



0086

Colas Ltd, Rowfant, Crawley, West Sussex RH10 4NF

Carnsew Quarry

12

0086-CPD-590156

DoP/CQ/M9004

EN 13108-1: 2006

M9004

AC 6 open surf 160/220

Intended to be used for Surface Course

Target grading passing sieve

Sieve (mm)	Passing (%)
10	100
6.3	98
2	24
1	14
0.063	2.0

Target binder content (%)	6.0
Minimum temperature (°C)	130
Maximum Temperature (°C)	170