



0086

Colas Ltd, Rowfant, Crawley, West Sussex RH10 4NF

Carnsew Quarry

12

0086-CPD-590156

DoP/CQ/S1004

EN 13108-5: 2006

S1004

SMA 10 surf 100/150 PSV65

Intended to be used for Surface Course

Target grading passing sieve

Sieve (mm)	Passing (%)
14	100
10	95
6.3	42
2	24
0.063	9.0

Target binder content (%)	6.4
Minimum void content	Vmin1.5
Maximum void content	Vmax5
Minimum temperature (°C)	130
Maximum Temperature (°C)	170
Binder Drainage	D0.3