



0086

Colas Ltd, Rowfant, Crawley, West Sussex RH10 4NF

Carnsew Quarry

12

0086-CPD-590156

DoP/CQ/S1006

EN 13108-5: 2006

**S1006**

SMA 10 surf 40/60

**Intended to be used for Surface Course**

Target grading passing sieve

Sieve (mm)	Passing (%)
14	100
10	93
6.3	45
2	22
0.063	10.0

Target binder content (%)	6.5
Minimum void content	Vmin1.5
Maximum void content	Vmax5
Minimum temperature (°C)	160
Maximum Temperature (°C)	200
Binder Drainage	D0.3