



0086

Colas Ltd, Rowfant, Crawley, West Sussex RH10 4NF

Carnsew Quarry

12

0086-CPD-590156

DoP/CQ/S1018

EN 13108-5: 2006

S1018

SMA 10 surf 40/60 PSV57

Intended to be used for Surface Course

Target grading passing sieve

| Sieve (mm) | Passing (%) |
|------------|-------------|
| 14 | 100 |
| 10 | 94 |
| 6.3 | 45 |
| 2 | 22 |
| 0.063 | 10.0 |

| | |
|---------------------------|---------|
| Target binder content (%) | 6.5 |
| Minimum void content | Vmin1.5 |
| Maximum void content | Vmax5 |
| Minimum temperature (°C) | 160 |
| Maximum Temperature (°C) | 200 |
| Binder Drainage | D0.3 |