



0086

Colas Ltd, Rowfant, Crawley, West Sussex RH10 4NF

Carnsew Quarry

12

0086-CPD-590156

DoP/CQ/S1026

EN 13108-5: 2006

S1026

SMA 10 surf 40/60 MoD Spec

Intended to be used for Surface Course

Target grading passing sieve

Sieve (mm)	Passing (%)
14	100
10	95
6.3	48
4	34
2	28
0.5	18
0.063	9.0

Target binder content (%)	6.6
Minimum void content	Vmin2.0
Maximum void content	Vmax4
Water sensitivity	ITSR70
Minimum temperature (°C)	160
Maximum Temperature (°C)	200
Binder Drainage	D0.3