



0086

Colas Ltd, Rowfant, Crawley, West Sussex RH10 4NF

Carnsew Quarry

12

0086-CPD-590156

DoP/CQ/S1031

EN 13108-5: 2006

S1031

Colpave 10 surf Colflex N PSV68

Intended to be used for Surface Course

Target grading passing sieve

Sieve (mm)	Passing (%)
14	100
10	95
6.3	42
2	24
0.5	15
0.063	9.0

Target binder content (%)	6.4
Minimum void content	Vmin1.5
Maximum void content	Vmax5
Resistance to Permananet Deformation	WTSair1.0
Water sensitivity	ITSR70
Minimum temperature (°C)	150
Maximum Temperature (°C)	180
Binder Drainage	BD0.3