



0086

Colas Ltd, Rowfant, Crawley, West Sussex RH10 4NF

Carnsew Quarry

12

0086-CPD-590156

DoP/CQ/S1033

EN 13108-5: 2006

**S1033**

SMA 10 surf Drive 40/60

Intended to be used for Surface Course

Target grading passing sieve

Sieve (mm)	Passing (%)
14	100
10	93
6.3	50
2	28
0.063	9.0

Target binder content (%)	6.5
Minimum temperature (°C)	160
Maximum Temperature (°C)	200