



0086

Colas Ltd, Rowfant, Crawley, West Sussex RH10 4NF

Carnsew Quarry

12

0086-CPD-590156

DoP/CQ/S1419

EN 13108-5: 2006

S1419

SMA 14 surf 100/150 PSV57

Intended to be used for Surface Course

Target grading passing sieve

Sieve (mm)	Passing (%)
20	100
14	95
10	47
6.3	28
2	22
0.063	9.0

Target binder content (%)	6.0
Minimum void content	Vmin1.5
Maximum void content	Vmax5
Minimum temperature (°C)	130
Maximum Temperature (°C)	170
Binder Drainage	D0.3