



0086

Colas Ltd, Rowfant, Crawley, West Sussex RH10 4NF

Carnsew Quarry

12

0086-CPD-590156

DoP/CQ/T1001

EN 13108-2: 2006

T1001

BBTM 10 B 70/100 PSV65

Intended to be used for Surface Course

Target grading passing sieve

Sieve (mm)	Passing (%)
14	100
10	97
6.3	43
4	28
2	23
1	17
0.063	4.5

Target binder content (%)	5.4
---------------------------	-----

Minimum temperature (°C)	140
--------------------------	-----

Maximum Temperature (°C)	180
--------------------------	-----