



# PRODUCTS

PROVIDING SAFE AND SUSTAINABLE SOLUTIONS



WE OPEN THE WAY

Colas Limited operates throughout the UK supplying an extensive range of products to local markets from strategically located depots.

With over 90 years in manufacturing within the bitumen emulsion market, Colas is able to draw on a vast level of experience and knowledge which is complimented by a strong focus on **research and development**.

As a result the company has built up unrivalled expertise in product manufacture, application techniques and specialist equipment. Colas are committed towards delivering innovation across a number of market sectors with the aim of achieving **sustainable solutions** for our customers enabling them to deliver best value.

Colas provides an extensive portfolio of products for use in the following Market Sectors:

- > Highway Maintenance
- > Local Authorities
- > Surfacing Contractors
- > Utilities
- > Civil Engineering
- > Toll Manufacturing

REINSTATEMENTS 7	OVERBANDING 25	ANTISKID 31
SEALANTS 41	FOOTWAY SURFACE TREATMENTS 51	SURFACE DRESSING BINDERS 57
BOND COATS 68	MORTARS 75	ANCILLARY 84

PRODUCTS DESIGNED TO PROVIDE

# SAFE AND SUSTAINABLE SOLUTIONS.

Our technical expertise is supported by the highest regard for **safety, quality and customer care**. In view of the constant development being undertaken in our laboratories, we advise customers in their own interests to ensure that this guide is the latest publication.

All products are sold subject to our standard conditions of sale which are available on request. No responsibility will be accepted for the use of any of our product(s), which is not in accordance with our current recommendations. For further information or for on-site advice please call our National Sales Office:

T: 01925 632616.

# COLAS LOCAL DEPOT NETWORK

All Colas products are manufactured in accordance with a Quality System certified to ISO9001 and are available through the Company's National Sales Office or network of local depots as well as independent stockists, details of which are available on request.



## REINSTATEMENTS

Bitucrete	8
Colpatch	10
Bitukold	12
RS Bitukold	13
RS Bitukold Spray	14
Colspray	15
H4	16
H4 Polymer	17
Preformed Road Markings	18
Eurolines	20
Patchmaster 100	22
Patchmaster 200	23
Colseal	24



**Bitucrete** is a deferred set, storage grade macadam for use as a first time permanent repair material in footways, footpaths and cycle tracks. It is also ideal for instant high quality temporary repairs on carriageways. **Bitucrete** is cold applied and therefore safe to handle.

Available in a variety of grades, **Bitucrete** can be used for footway repairs, patching, reinstatements and temporary surfacing. **Bitucrete** provides an immediate cure for potholes in car parks, roads, drives, factory floors and many other surfaces.

**Bitucrete** is a combination of paving grade bitumen's, additives and selected aggregates. High PSV granite or basalt aggregate makes it suitable for all classes of road and footway. Available in black and red.

## WHERE TO USE?

- Patches potholes in bituminous surfaces
- Reinstates trenches in lightly trafficked surfaces
- Provides temporary ramping for high kerbs and exposed ironwork
- Fills worn areas in paths and drives

## PREPARATION

Ensure that the surface to be repaired is clean and free from loose material, oil, grease and standing water. Prime base surface with **Leotak**.

Edges of the area to be repaired should be formed vertically as far as possible and then treated with **Bitukold**, **RS Bitukold** or **RS Bitukold Spray** edge sealant prior to forming joints. For small potholes, **Bitukold**, **RS Bitukold** or **RS Bitukold Spray** may be used over the surface area of the hole as a tack coat.

Workability can be ensured even in cold weather by simply manipulating the **Bitucrete** in its sealed bag. N.B: To aid workability of bagged **Bitucrete** in winter, store bags in a warm area (>10°C ambient temperature) for 24 hours prior to use if possible.

## APPLICATION

Tip sufficient **Bitucrete** from the bag to over-fill the hole, ensuring that all corners are filled.

Compact the material to the surrounding level using a compactor, roller or hand tamper depending on the nature of the site. For large areas use a vibrating plate or roller slightly wetting the drum with water. If under-filling has taken place, simply add more product and compact to level. Material should not be laid any deeper than 2 1/2 times the size of the nominal stone in any one layer.

The repair will withstand immediate heavy trafficking, however, where the repair is to be crossed by fork-lift trucks and HGVs, extra compaction and curing time must be allowed.

**Bitucrete** remains flexible for some time after application. Curing is brought about by both air drying and compaction. The rate of cure is dependent upon temperature as well as the weight and volume of traffic. However, under normal traffic conditions, **Bitucrete** will not depress, track or pick up during the curing process.

As the material will take up the contours of potholes naturally and form an immediate repair, it is ideal for irregularly shaped potholes. **Bitucrete** is also suitable for temporary ramping of exposed ironwork.

Grade	Nominal Size	Material Specification
4mm	0/4mm	AC 4 fine surf 160/220DS
6mm	0/6mm	AC 6 med surf 160/220DS
6mm (Red)	0/6mm	AC 6 med surf 160/220DS
10mm	0/10mm	AC 10 close surf 160/220DS

## COVERAGE

The table below shows the approximate rate of spread of various compacted thicknesses of **Bitucrete**. Please note that the covering capacity of **Bitucrete** may be affected by such factors as the density and grading of the aggregates, condition of the substrate and final state of compaction. On more irregular substrates, heavier rates of spread are to be expected.

Spread Rate Guide	
Average thickness of course (mm)	Coverage (m <sup>2</sup> /t)
20	18 to 24
25	15 to 19
30	13 to 15
35	11 to 13
40	10 to 12
45	9 to 11
50	8 to 10
60	7 to 8.5
70	6 to 7.5
75	5 to 6.5
100	4 to 5

## PACKAGING

**Bitucrete** is available in 25kg sealed plastic bags (40 x 25kg per pallet).

## STORAGE

**Bitucrete** has a storage life of up to six months in sealed bags and under good storage conditions. Bags are batch numbered for easy stock rotation.

## STANDARDS

**Bitucrete** complies with BS EN 13108-1 Bituminous Mixtures. Material Specification. Asphalt Concrete.

## SAFETY

For full safety information, please request the **Bitucrete** Safety Data Sheet 03b using the contact information at the back of this brochure.

# COLPATCH

# COLPATCH



**Colpatch** is a BBA HAPAS approved, cold applied storage grade macadam that is ideal for instant, high quality repairs to bituminous and concrete surfaces.

**Colpatch** is formulated from paving grade bitumen, selected aggregates and Macfix additive supplied under licence by Macismo Asphalt & Innovation. This unique additive results in flexibility within the repair reducing the risk of reflective cracking. It also provides the long storage properties of **Colpatch** which enables the remaining material to be stockpiled externally all year round without deterioration and remains workable in cold weather conditions

**Colpatch** is easy to use with no mixing required with a long storage life of up to two years. To accommodate the customer's storage capability the material is available in a variety of options.

## WHERE TO USE?

- Patches/potholes in bituminous surfaces
- Reinstates trenches in trafficked surfaces
- Carriageway repairs
- Reinstatements and temporary surfaces

## PREPARATION

Ensure that the surface to be repaired is clean and free from loose material, oil, grease and standing water.

To achieve a long lasting repair it is recommended that the base surface is primed with **Leotak**. Edges of the area to be repaired should be vertically formed as far as possible and then treated with a **Bitukold Spray** edge sealant prior to forming joints. For small potholes, **Bitukold** or **RS Bitukold** may be used over the surface area of the hole as a tack coat. However a quick repair can be performed without any cutting out, tack coats or edge sealants.

## APPLICATION

Apply sufficient **Colpatch** to over-fill the area to be reinstated, ensuring that all corners are filled by gently kneading the material with a shovel to evenly spread it across the full area.

Compact the material to the surrounding level using a hand tamper or compactor/roller. For large areas and deep sections, use a vibrating plate or roller slightly wetting the drum with water. If under-filling has taken place, simply add more product and compact to level.

It is recommended that deep patches should be built up in 15-40mm compacted layers as this will result in better compaction being achieved.

Once compacted the **Colpatch** is ready to be trafficked. Curing is brought about by both air drying and compaction, with the rate of cure dependent upon temperature and the weight and volume of traffic. However, under normal traffic conditions, **Colpatch** will not depress, track or pick up during the curing process.

**Colpatch** remains flexible for some time after application as the material will take up the contours of potholes naturally and form an immediate repair, it is ideal for irregularly shaped potholes.



## COVERAGE

The below table shows the approximate rate of spread of various compacted thicknesses of **Colpatch**.

Spread Rate Guide	
Average thickness of course (mm)	Coverage (m <sup>2</sup> /t)
20	22 to 28
30	15 to 19
40	11 to 15
50	9 to 12
60	8 to 10
75	6 to 8
100	4 to 6

Please note that the covering capacity of **Colpatch** may be affected by such factors as the density and grading of the aggregates, condition of the substrate and final state of compaction. On more irregular substrates, heavier rates of spread are to be expected.

## PACKAGING

**Colpatch** is available in bulk loads, 1 tonne bulk bags, 25kg sealed bags (40 x 25kg per pallet) and 25kg sealed buckets (36 x 25kg per pallet).

## STORAGE

Keep free from frost and extremes of heat.

## STANDARDS

**Colpatch** is BBA HAPAS Approved Certificate 11/H179

## SAFETY

For full safety information, please request the **Colpatch** Safety Data Sheet 03c using the contact information at the back of this brochure.



Licensed from  
Macismo Asphalt Innovations



# BITUKOLD



**Bitukold** is a cold hand applied, thixotropic bitumen emulsion designed for sealing vertical joints. On small patches, **Bitukold** can also be used as a tack coat, thereby saving on the need to use a separate tack coat emulsion. **Bitukold** is mainly used for the protection of new joints in freshly laid asphalt or macadam.

## WHERE TO USE?

- Transverse or longitudinal vertical joints
- Trench reinstatements
- Patch repairs
- Drain or manhole frames and exposed ironwork
- Kerb channels

## PREPARATION

**Bitukold** should not be applied in ambient temperatures of less than 5°C. Ensure surface is clean and free from loose material, oil, grease, standing water and weeds.

## APPLICATION

A soft fibre or turks head brush should be used to apply the **Bitukold**. The brush must be dampened using clean water and any excess shaken off before commencing application. Then using a full brush of material, apply evenly in one direction, covering the whole face of the joint. In very hot weather application will be easier if the joint surface is slightly dampened.

In normal conditions surfacing can commence within 15 minutes. The application of hot material rapidly completes the drying. Drying will be delayed in cold, damp and humid weather.

Wash the brushes immediately after use with soapy water followed by **Leoclean**.

## COVERAGE

On vertical joints 1.5kg/m<sup>2</sup> gives a dried film thickness of 1mm. For joints 50mm deep, a 15kg bucket covers approximately 200 linear metres of joint. Saw cutting the edge of the joint will maximise the rate of spread. As a tack coat in small patches and potholes a spread rate of 0.25-0.45kg/m<sup>2</sup> should be achieved.

## PACKAGING

**Bitukold** is available in re-sealable 15kg yellow lidded buckets (36 x 15kg per pallet).

## STORAGE

Protect from frost or extremes of heat. **Bitukold** has a storage life of up to six months in sealed buckets under good storage conditions.

## STANDARDS

**Bitukold** complies with BS 594987 Clause 6.8 Joints, vertical face coating, and is suitable for jointing as required in clause 903.2 (iii) of the Specification of Highway Works.

## SAFETY

For full safety information, please request the **Bitukold** Safety Data Sheet 04 using the contact information at the back of this brochure.

# RS BITUKOLD



**RS Bitukold** is a rapid setting, cold applied thixotropic bitumen emulsion designed for sealing vertical joints. The cationic formulation of **RS Bitukold** ensures a rapid set even in cold, damp conditions, with an initial cure taking place within 15 minutes. **RS Bitukold** is mainly used for the protection of new joints in freshly laid asphalt or macadam.

## WHERE TO USE?

- Transverse and longitudinal vertical joints
- Horizontal cracks in asphaltic roads
- Trench reinstatements
- Patch repairs
- Drain or manhole frames
- Kerb channels

## PREPARATION

**RS Bitukold** should not be applied in ambient temperatures of less than 5°C. Ensure surface is clean and free from loose material, oil, grease, standing water and weeds.

## APPLICATION

**RS Bitukold** can be applied by pouring from a spouted watering can or, alternatively, spray applied through the **Roadmaster Sprayer**.

## COVERAGE

**RS Bitukold** should be applied at a rate of 0.7 - 1.5kg/m<sup>2</sup> depending upon the texture and porosity of the surface and the application method.

For joints 50mm deep, a 15kg bucket covers approximately 200 linear metres. Saw cutting the edge of the joint will maximise the rate of spread.

## PACKAGING

**RS Bitukold** is available in re-sealable 15kg black lidded buckets (36 x 15kg per pallet) or cardboard boxes containing 60 x 10kg bags.

## STORAGE

Protect from frost or extremes of heat. **RS Bitukold** has storage life of up to six months in sealed buckets under good storage conditions.

## STANDARDS

**RS Bitukold** is a CE Marked cationic emulsion to BS EN13808:2013 C60B3/4 or C65B3/4. **RS Bitukold** also complies with BS 594987 Clause 6.8 Joints, vertical face coating, and is suitable for jointing as required in clause 903.2 (iii) of the Specification of Highway Works.

Full CE Marking information is available from the Colas Products website.  
[www.colasproducts.co.uk](http://www.colasproducts.co.uk)

## SAFETY

For full safety information, please request the **RS Bitukold** Safety Data Sheet 93 using the contact information at the back of this brochure.

# RS BITUKOLD SPRAY



**RS Bitukold Spray** is a rapid setting, cold applied bitumen emulsion designed for sealing vertical joints. The cationic formulation of **RS Bitukold Spray** ensures a rapid set even in cold, damp conditions, with an initial cure taking place within 15 minutes.

## WHERE TO USE?

- Transverse and longitudinal vertical joints
- Trench reinstatements
- Patch repairs
- Drain or manhole frames
- Kerb channels

## PREPARATION

Ensure that the surface is clean and free from loose materials, oil, grease, standing water and weeds.

## APPLICATION

Shake can vigorously before use. Turn can upside down and apply **RS Bitukold Spray** in even strokes with nozzle 200-300mm away from the surface to be treated. Ensure complete coverage. After use spray briefly with can in upright position to clear nozzle.

## COVERAGE

The coverage rate for **RS Bitukold Spray** should be 0.7 - 1.5 kg/m<sup>2</sup>, depending on the texture and porosity of the surface.

## PACKAGING

**RS Bitukold Spray** is supplied in 600ml aerosol cans (12 per box).

## STORAGE

- Caution: pressurised container, protect from sunlight
- Do not pierce or burn even after use
- Do not expose to temperatures exceeding 50°C
- Do not spray on a naked flame or any incandescent material
- Keep out of reach of children
- Store in an upright position

## STANDARDS

**RS Bitukold Spray** complies with BS 594987: Clause 6.8 Joints, vertical face coating.

## SAFETY

For full safety information, please request the **RS Bitukold Spray** Safety Data Sheet 54 using the contact information at the back of this brochure.

# COLSPRAY



## COVERAGE

The coverage rate for **Colspray** should be 0.7 to 1.5 kg/m<sup>2</sup>, depending on the texture and porosity of the surface.

## PACKAGING

**Colspray** is supplied in 750ml aerosol cans (12 per pack).

## STORAGE

- Caution: pressurised container, protect from sunlight
- Do not pierce or burn even after use
- Do not expose to temperatures exceeding 50°C
- Do not spray on a naked flame or any incandescent material
- Keep out of reach of children

## STANDARDS

**Colspray** complies with BS 594987 Clause 6.8 joints, vertical face coating.

## SAFETY

For full safety information, please request the **Colspray** Safety Data Sheet 149 using the contact information at the back of this brochure.

**Colspray** is a rapid setting, cold applied bitumen spray designed for sealing vertical joints. **Colspray** can also be used as a tack coat helping to prevent the ingress of water.

## WHERE TO USE?

- Transverse or longitudinal vertical joints
- Trench reinstatements
- Patch repairs
- Drain or manhole frames
- Kerb channels

## PREPARATION

Ensure that the surface is clean and free from loose materials, oil, grease, standing water and weeds.

## APPLICATION

Shake can vigorously before use. Turn can upside down and apply **Colspray** in even strokes with nozzle 200-300mm away from the surface to be treated. Ensure complete coverage. After use spray briefly with can in upright position to clear nozzle.





**H4** is a hot poured joint sealant designed for the treatment of reinstatements and asphalt overlays.

## WHERE TO USE?

- Transverse or longitudinal vertical joints
- Patch repairs
- Trench reinstatements
- Drain or manhole frames
- Kerb channels

## PREPARATION

Ensure that the joints to be sealed are clean and free from dust, fuel and oil spillage. The face of the joints should be dry with a surface temperature ideally of at least 10°C. Do not apply to icy surfaces or in rain.

## APPLICATION

**H4** must be heated before use. For best results, use a heating kettle with an indirect heating system such as hot oil. Ensure that **H4** doesn't exceed 200°C and that the oil does not exceed 230°C. When hot, pour either from a watering can or direct from the melting kettle via a pressure fed heated hose with a special nozzle. The 25kg tin pails are not suitable for placing on or over direct heat (i.e. gas or wood fire).

## COVERAGE

For a 40mm vertical joint face and a 2mm coated thickness of **H4**, 0.08kg, seals approximately one linear metre of joint or a 25kg pack seals approximately 300 linear metres of joint.

## PACKAGING

**H4** is supplied in 25kg siliconized easy strip cartons (20 x 25kg per pallet) or 12.5kg siliconized easy strip cartons (40 x 12.5kg per pallet) and in 25kg metal pails with handles (24 x 25kg per pallet) being leak proof, these pails are particularly convenient for use during hot weather.

## STORAGE

Keep free from frost and extremes of heat. Do not stack. Do not store in direct sunlight.

## STANDARDS

**H4** is a CE Marked paving grade bitumen complying to BS EN12591:2009 which also complies with BS 594987 Clause 6.8 Joints. **H4** is suitable for jointing as required in clause 903.22(i) of Volume 1 of the Specification for Highway Works.

Full CE Marking information is available from the Colas Products website.  
[www.colasproducts.co.uk](http://www.colasproducts.co.uk)

## SAFETY

### SAFETY HANDLING PRECAUTIONS (when hot)

- Wear suitable protective clothing (heat resistant gauntlet gloves, overalls, protective footwear, face visor)
- DO NOT allow water to contact hot material
- DO NOT exceed maximum safe heating temperature
- If molten material contacts skin:
  - DO NOT attempt to remove
  - Immerse affected area in cold running water for at least 10 minutes
  - Seek medical advice without delay
- This product is hazardous for transportation when carried at temperatures above 100°C

For full safety information, please request the **H4** Safety Data Sheet 12 using the contact information at the back of this brochure.



**H4 Polymer** is a modified hot poured joint sealant designed for the treatment of reinstatements and asphalt overlays giving greater flexibility to the joint.

## WHERE TO USE?

- Transverse or longitudinal vertical joints
- Patch repairs
- Trench reinstatements
- Drain or manhole frames
- Kerb channels

## PREPARATION

Ensure that the joints to be sealed are clean and free from dust, fuel and oil spillage. The face of the joints should be dry with a surface temperature ideally of at least 10°C. Do not apply to icy surfaces or in rain.

## APPLICATION

**H4 Polymer** must be heated before use. For best results, use a heating kettle with an indirect heating system such as hot oil. Ensure that **H4 Polymer** doesn't exceed 200°C and that the oil does not exceed 230°C. When hot, pour either from a watering can or direct from the melting kettle via a pressure fed heated hose with a special nozzle. The 25kg tin pails are not suitable for placing on or over direct heat (i.e. gas or wood fire).

## COVERAGE

For a 40mm vertical joint face and a 2mm coated thickness of **H4 Polymer**, 0.08kg, seals approximately one linear metre of joint or a 25kg pack seals approximately 300 linear metres of joint.

## PACKAGING

**H4 Polymer** is supplied in 25kg metal pails with handles (24 x 25kg per pallet) being leak proof, these pails are particularly convenient for use during hot weather.

## STORAGE

Keep free from frost and extremes of heat. Do not stack. Do not store in direct sunlight.

## STANDARDS

**H4 Polymer** is a CE Marked paving grade bitumen complying to BS EN14023:2010 which also complies with BS 594987 Clause 6.8 Joints. **H4 Polymer** is suitable for jointing as required in clause 903.22(ii) of Volume 1 of the Specification for Highway Works.

Full CE Marking information is available from the Colas Products website.  
[www.colasproducts.co.uk](http://www.colasproducts.co.uk)

## SAFETY

### SAFETY HANDLING PRECAUTIONS (when hot)

- Wear suitable protective clothing (heat resistant gauntlet gloves, overalls, protective footwear, face visor)
- DO NOT allow water to contact hot material
- DO NOT exceed maximum safe heating temperature
- If molten material contacts skin:
  - DO NOT attempt to remove
  - Immerse affected area in cold running water for at least 10 minutes
  - Seek medical advice without delay
- This product is hazardous for transportation when carried at temperatures above 100°C

For full safety information, please request the **H4 Polymer** Safety Data Sheet 56H using the contact information at the back of this brochure.

# PREFORMED ROAD MARKINGS



**Prefomed Road Markings** are skid resistant thermoplastic symbols, letters and numbers. **Prefomed Road Markings** are non-toxic, contain no lead or chromate pigments and are skid resistant to >55 SRV.

## WHERE TO USE?

- Roads
- Car parks
- Playgrounds
- Cycle lanes

## PREPARATION

**Prefomed Road Markings** are easy to apply to bituminous and concrete surfaces. Before application, always ensure that the area is clean, dry and free from dust, oil and fuel residues. **Pre-mark Primer** is required for concrete, stone and worn macadam surfaces.

Ensure that the primer is completely dry before the material is applied. In cold conditions warming of the surface prior to application is required to enhance adhesion.

Clean area where **Prefomed Road Markings** are to be applied thoroughly by removing all sand, dirt, chemicals and oily substances. If there is any moisture present in the surface this must be removed with the gas burner.

## APPLICATION

Place the **Prefomed Road Markings** on the surface with the beaded top coat facing up. Make sure the individual pieces are positioned correctly and with no gaps in-between.

Heat the material using a powerful gas burner (pressure min. 3 bar). Move the flame slowly but steadily 10cm to 30cm over the material in a sweeping motion so that heat is evenly applied. The material must be heated until all the material is liquid (approx. 200°C).

Applying insufficient heat will result in inadequate bonding and failure. If overheated, superficial scorching of the material can occur by means of brown blotching, but this discolouring will soon disappear once the marking is exposed to traffic and weather.

## COVERAGE

Varies dependent upon the size and type of symbol, letter or number being installed.

## PACKAGING

**Prefomed Road Markings** are supplied in flat pack cardboard boxes. Some symbols and markings are supplied in pieces that may require assembly on-site.

## STORAGE

- Keep flat and store in a cool, dry place – between 2°C and 32°C
- Maximum of 25 packs high
- Shelf life in sealed packaging is 12 months
- In cold weather, application will be assisted by storing overnight at room temperature

# PREFORMED ROAD MARKINGS

## STANDARDS

Complies to EN 1436 Classes: S3, Q3, R3.

## SAFETY

SAFETY HANDLING PRECAUTIONS (when hot)

- Wear suitable protective clothing (heat resistant gauntlet gloves, overalls, protective footwear, face visor)
- DO NOT allow water to contact hot material
- DO NOT exceed maximum safe heating temperature
- If molten material contacts skin:
  - DO NOT attempt to remove
  - Immerse affected area in cold running water for at least 10 minutes
  - Seek medical advice without delay

For full safety information, please request the **Prefomed Road Markings** Safety Data Sheet 106 using the contact information at the back of this brochure.



**Eurolines** are skid resistant thermoplastic markings designed for demarcation and lining. **Eurolines** are non-toxic, contain no lead or chromate pigments and are skid resistant to >55 SRV.

## PREPARATION

**Eurolines** are easy to apply to bituminous and concrete surfaces. **Premark Primer** should be used when applying **Eurolines** to concrete, stone and worn macadam surfaces.

Ensure that the primer is completely dry before the material is applied. In cold conditions warming of the surface prior to application is required to enhance adhesion.

Clean area where **Eurolines** are to be applied thoroughly by removing all sand, dirt, chemicals and oily substances. If there is any moisture present in the surface this must be removed with the gas burner.

## APPLICATION

**Eurolines** should be placed on the surface with the beaded top coat facing up making sure the individual pieces are positioned correctly and with no gaps in-between.

The material should be heated using a powerful gas burner (pressure min. 3 bar). Move the flame slowly but steadily 10cm to 30cm over the material in a sweeping motion so that heat is evenly applied. The material must be heated until all the material is liquid (approx. 200°C).

Applying insufficient heat will result in inadequate bonding and subsequent failure of the material. If overheated, superficial scorching of the material can occur resulting in brown blotching, but this discolouring will soon disappear once the **Eurolines** are exposed to traffic and weather.

## COVERAGE

100mm x 5000mm  
50mm x 5000mm

## PACKAGING


**Eurolines** come in a variety of colours: White, Yellow, Primrose and Red in packs ready for use.

Each pack contains either:

- 6 (100mm x 5000mm) rolls
- 12 (50mm x 5000mm) rolls

## STORAGE

- Keep flat and store in a cool, dry place - between 2°C and 32°C
- Maximum of 25 packs high
- Shelf life in sealed packaging is 12 months
- In cold weather, application will be assisted by storing overnight at room temperature



## STANDARDS

Complies to EN 1436 Classes: S3, Q3, R3.

## SAFETY

SAFETY HANDLING PRECAUTIONS (when hot)

- Wear suitable protective clothing (heat resistant gauntlet gloves, overalls, protective footwear, face visor)
- DO NOT allow water to contact hot material
- DO NOT exceed maximum safe heating temperature
- If molten material contacts skin:
  - DO NOT attempt to remove
  - Immerse affected area in cold running water for at least 10 minutes
  - Seek medical advice without delay

For full safety information, please request the **Eurolines** Safety Data Sheet 106 using the contact information at the back of this brochure.

# PATCHMASTER 100



**Patchmaster 100** is a cationic bitumen emulsion specifically formulated to be used in conjunction with automated spray injection patching equipment and to be used with an approved aggregate. The emulsion is used both as a tack coat and as a binder in the spray injection patching operation. For higher stressed repairs use polymer modified **Patchmaster 200**.

## WHERE TO USE?

In conjunction with automated spray injection patching equipment.

## PREPARATION

See operators method statement.

## APPLICATION

**Patchmaster 100** is designed for use with specialist spray injection patching equipment and should only be used when the ground temperature is  $>5^{\circ}\text{C}$  and rising, and  $<40^{\circ}\text{C}$ . Humidity should preferably not exceed 70%, although **Patchmaster 100** can be applied in higher humidity and in colder temperatures but this will prolong the break time.

## COVERAGE

See operators method statement.

## PACKAGING

**Patchmaster 100** emulsion is available in bulk loads or 200kg drums.

## STORAGE

Protect from frost. Drums should be rolled frequently to avoid separation. Bulk material should be circulated before use. For further information please refer to BS434-2:2006, section 5 Clause 5.2 Storage.

## STANDARDS

**Patchmaster 100** is a CE Marked cationic bitumen emulsion complying to BS EN13808:2013 C60B4/5.

Full CE Marking information is available from the Colas Products website.

[www.colasproducts.co.uk](http://www.colasproducts.co.uk)

Emulsion	
Binder content (EN 1428)	58 - 62% (Class 6)
Efflux 2mm @ 40°C (EN 12846-1)	15 - 70 s (Class 3)
Water effect on binder adhesion (EN 13614)	$\geq 90$ (Class 3)
Breaking behaviour (EN 13075-1)	110 - >170 (Class 4/5)

## SAFETY

For full safety information, please request the **Patchmaster 100** Safety Data Sheet 46 using the contact information at the back of this brochure.

# PATCHMASTER 200



**Patchmaster 200** is a polymer modified cationic bitumen emulsion specifically formulated to be used in conjunction with automated spray injection patching equipment and to be used with an approved aggregate. The emulsion is used both as a tack coat and as a binder in the spray injection patching operation and is ideal for higher stress repairs.

## WHERE TO USE?

In conjunction with automated spray injection patching equipment.

## PREPARATION

See operators method statement.

## APPLICATION

**Patchmaster 200** is designed for use with specialist spray injection patching equipment and should only be used when the ground temperature is  $>5^{\circ}\text{C}$  and rising, and  $<40^{\circ}\text{C}$ . Humidity should preferably not exceed 70%, although **Patchmaster 200** emulsion can be applied in higher humidity and in colder temperature but this will prolong the break time.

## COVERAGE

See operators method statement.

## PACKAGING

**Patchmaster 200** emulsion is available in bulk loads or 200kg drums.

## STORAGE

Protect from frost. Drums should be rolled frequently to avoid separation. Bulk material should be circulated before use. For further information please refer to BS434-2:2006, Section 5 Clause 5.2 Storage.

## STANDARDS

**Patchmaster 200** is a CE Marked cationic bitumen emulsion to BS EN13808:2013 C60BP4/5.

Full CE Marking information is available from the Colas Products website.

[www.colasproducts.co.uk](http://www.colasproducts.co.uk)

Emulsion	
Binder content (EN 1428)	58 - 62% (Class 6)
Efflux 2mm @ 40°C (EN 12846-1)	15 - 70 s (Class 3)
Water effect on binder adhesion (EN 13614)	$\geq 90$ (Class 3)
Breaking behaviour (EN 13075-1)	110 - >170 (Class 4/5)
Recovered Binder	
Penetration @ 25°C (EN 1426)	$\leq 220$ - $\leq 330$ dmm (class 5/6/7)
Softening point (EN 1427)	$\geq 39^{\circ}\text{C}$ (Class 7)
Cohesion by pendulum (EN 13588)	$\geq 0.75/\text{cm}^2$ (Class 5)

## SAFETY

For full safety information, please request the **Patchmaster 200** Safety Data Sheet 46 using the contact information at the back of this brochure.

# COLSEAL



**Colseal** is a pre-mixed slurry seal for sealing utility reinstatement and patch repairs. It is also ideal for sealing pre-surface dressing patches. It can also be used for covering score marks and for the treatment of driveways and pathways.

## WHERE TO USE?

- Carriageways
- Footways
- Driveways

## PREPARATION

The surface should be clean, dry and free of any loose chippings/debris (the treatment and removal of any weeds and moss should be carried out prior to laying preparation). Use masking tape to protect any kerbs/ironwork etc. from being covered (this is to be removed while the **Colseal** is still wet).

## APPLICATION

Mix thoroughly before use using a drill paddle.

Pour onto surface in manageable amounts and using a soft brush with handle or squeegee, spread evenly over the surface to the recommended thickness of approximately 1.5-2mm, promptly finishing this area in the same directional brush stroke.

If a thickness greater than 1.5-2mm is required we recommend an additional application but it must be ensured that the first application is set fully before reapplying.

The material should be applied on a dry day at temperatures of 10°C and rising with no possibility of rainfall. Setting times vary with temperature. At the recommended thickness setting times will be, at 25°C approximately 1-3 hours and at 10°C 3-6 hours.

## COVERAGE

1 x 25kg bag will cover approximately 10-14m<sup>2</sup> @ 1.5 - 2mm thickness, depending on surface texture.

## PACKAGING

**Colseal** is supplied in 25kg buckets (36 x 25kg per pallet) or cardboard boxes containing 40 x 25kg bags.

## STORAGE

Store in a cool, dry place, protect from frost.

## STANDARDS

Supplied in accordance to ISO9001.

## SAFETY

For full safety information, please request the **Colseal** Safety Data Sheet 152 using the contact information at the back of this brochure.



# OVERBANDING

Colstrips	26
Gripstrip	27
Jointgrip OB	28
GripRoll	30

# COLSTRIPS



**Colstrips** are BBA HAPAS approved skid resistant overbanding and crack sealing thermoplastic strips, designed to seal and repair static cracks up to 5mm wide and 20mm deep in nonporous bituminous and concrete highways.

**Colstrips** seal patches and reinstatements preventing the ingress of water helping to extend the life of the repair. **Colstrips** are easy to apply with no wastage and can be trafficked almost immediately. **Colstrips** are non-toxic, contain no lead or chromate pigments and are skid resistant to >65 SRV.

## WHERE TO USE?

- Overbanding for patches and reinstatements

## PREPARATION

**Colstrips** are easy to apply to bituminous and concrete surfaces. Before application always ensure the area is clean, dry and free from dust and oily residues. Concrete surfaces should be primed with **CP Primer** ensuring that the primer is completely dry before the **Colstrips** are applied.

## APPLICATION

Preheat the surface making sure it is free from moisture, remove **Colstrips** from their protective wrapping and place on the road surface.

Heat the **Colstrips** with a propane torch using a slow sweeping motion, making sure that you do not spot heat any areas as this may scorch the material.

**Colstrips** must be heated until they start to bubble.

The material will cool and harden within 5-10 minutes of installation.

Applying insufficient heat will result in inadequate bonding and subsequent failure of the material.

## COVERAGE

1 metre lengths.

## PACKAGING

**Colstrips** are supplied in flat pack cardboard boxes, each box contains 80 (1000mm x 35mm) strips.

## STORAGE

- Keep flat and store in a cool, dry place – between 2°C and 32°C
- Maximum of 25 packs high
- Shelf life in sealed packaging is 12 months
- In cold weather, application will be assisted by storing overnight at room temperature

## STANDARDS

Complies to EN 1436 Classes: S5.

## SAFETY


SAFETY HANDLING PRECAUTIONS (when hot)

- Wear suitable protective clothing (heat resistant gauntlet gloves, overalls, protective footwear, face visor)
- DO NOT allow water to contact hot material
- DO NOT exceed maximum safe heating temperature
- If molten material contacts skin:
  - DO NOT attempt to remove
  - Immerse affected area in cold running water for at least 10 minutes
  - Seek medical advice without delay

For full safety information, please request the **Colstrips** Safety Data Sheet 106 using the contact information at the back of this brochure.



# GRIPSTRIPS



**Gripstrip** is an anti-skid, self-adhesive, overbanding joint and crack sealing tape. **Gripstrip** consists of an extruded bituminous compound modified with elastomers and fast bonding resins.

## WHERE TO USE?

- Horizontal cracks in asphaltic roads
- Transverse and longitudinal joints
- Trench reinstatements
- Patch repairs
- Drain or manhole frames

## PREPARATION

Ensure that the joint or crack is dry, clean and free from dust, fuel and oil spillage. For best results use when ambient temperature is 15°C or above. **Gripstrip** should not be applied to cracks wider than 10mm unless the crack has been pre-filled with approved material such as **Jointfill A2**, **Jointfill N1 & N2** or **Leoseal R**.

## APPLICATION

**Gripstrip** is applied to the road surface manually or with a specially adapted trolley. It is self-adhesive with the underside protected by peel off backing paper.

Once laid heavy foot pressure should be applied to assist adhesion. Applied **Gripstrip** will become embedded through trafficking.

## COVERAGE

Each roll will overband 25 linear metres.

## PACKAGING

**Gripstrip** is supplied in a box with 2 x 40mm x 25m rolls.

## STORAGE

Keep in dry store under cover.

## STANDARDS

**Gripstrip** has a skid resistance value of  $\geq 60$  and therefore complies with the requirements of the New Roads and Street Works Act.

## SAFETY

For full safety information, please request the **Gripstrip** Safety Data Sheet 94 using the contact information at the back of this brochure.



**Jointgrip OB** is an anti-skid overbanding joint sealant. It is a proprietary formulation of blended paving grade bitumen incorporating special polymers and abrasive aggregates to provide a compound of toughness, flexibility, adhesiveness and resistance to flow.

## WHERE TO USE?

- Horizontal cracks in concrete and asphaltic roads
- Transverse and longitudinal joints
- Airfield surfaces where extra protection is required beyond edges or joints or cracks
- Trench reinstatements
- Patch repairs

## PREPARATION

Ensure that the joint or crack to be treated is dry, clean and free from dust, fuel and oil spillage. For best results cracks to be sealed should be thoroughly cleaned and dried using a hot compressed air lance, grit-blasting or power brushing to remove all detritus. Do not apply to icy surfaces or in cold, damp conditions.

## APPLICATION

**Jointgrip OB** should be heated and agitated in a purpose built temperature controlled bitumen preheater and horizontal mixer unit ensuring that the temperature does not exceed 200°C.

The material should be discharged within the specified pouring temperature (170-190°C) into a pre-warmed suitable pouring bucket and then into an overbanding shoe of the appropriate width and applied at a thickness which should be between 2-2.5mm.

Alternatively, for small sites a heavy duty metal bucket may be used with a pourer lip, positioned on a purpose-built stand with gas ring. **Jointgrip OB** will need to be broken up and heated in the bucket to just pourable temperature and agitated with a flat metal stirrer, having one end curved to enable aggregate to be kept suspended.

N.B: Agitate the material in the bucket from time to time to avoid localised over-heating and aggregate separation (Warning: do not over-heat).

Density (SG)	1.5kg/ltr
Application/pouring temperature	170 - 190°C
Safe heating temperature	190°C
Flash point	>250°C
Softening point	85°C
Flow (ASTM Plate)	≤5mm

## PROPERTIES

If required an application of sand whilst hot will remove reflectivity (gloss) of the finished overband - however, the initial gloss finish of the product diminishes soon after trafficking.

## COVERAGE

When used as an overbanding on reinstatement joints, reflective and small cracks, 1000kgs will overband approximately 3500 linear metres at 40mm width, 2.5mm height.

Rate of use may increase dependent on application.

## PACKAGING

**Jointgrip OB** is available in 25kg (approx.) paper sacks (40 x 25kg per pallet) and 12.5kg siliconized easy strip cartons (40 x 12.5kg per pallet).

## STORAGE

Keep in dry store under cover.

## STANDARDS

**Jointgrip OB** complies with the skid resistance value required by the new Roads and Street Works Act.

## SAFETY

### SAFETY HANDLING PRECAUTIONS (when hot)

- Wear suitable protective clothing (heat resistant gauntlet gloves, overalls, protective footwear, face visor)
- DO NOT allow water to contact hot material
- DO NOT exceed maximum safe heating temperature
- If molten material contacts skin:
  - DO NOT attempt to remove
  - Immerse affected area in cold running water for at least 10 minutes
  - Seek medical advice without delay

NB: This product is hazardous for transportation when carried at temperatures above 100°C.

For full safety information please request the **Jointgrip OB** Safety Data Sheet 35 using the contact information at the back of this brochure.

# GRIPROLL



**GripRoll** is a unique BBA HAPAS Approved skid resistant overbanding and crack sealing thermoplastic roll. **GripRoll** has been specially formulated to be more flexible at lower temperatures than standard thermoplastic rolls and is a marked improvement on the conventional glass grains producing a skid resistance value >70.

**GripRoll** is designed to seal and repair static cracks up to 5mm wide and 20mm deep in nonporous bituminous and concrete highways. **GripRoll** seals patches and reinstatements preventing the ingress of water helping to extend the life of the repair. **GripRoll** is easy to apply with no wastage and can be trafficked almost immediately.

## WHERE TO USE?

- Overbanding for patches and reinstatements

## APPLICATION

Preheat the surface making sure it is free from moisture, roll out the **GripRoll** and place on the road surface.

Where you are applying to a non-bituminous substrate, prime the surface with **Colas Thermo-Tac Primer** before rolling out the **GripRoll**.

Heat the **GripRoll** with a propane torch using a slow sweeping motion, making sure that you do not spot heat any areas as this may scorch the material.

**GripRoll** must be heated until it starts to bubble and melt then remove the heat. The material will cool and harden within 5-10 minutes of installation. Always check the **GripRoll** does not lift, if any areas do lift, apply more heat.

Applying insufficient heat will result in inadequate bonding and subsequent failure of the material.

## COVERAGE

Each roll is 5m x 35mm.

## PACKAGING

**GripRoll** is supplied in boxes, each box contains 12 rolls (5m x 35mm).

## STORAGE

- Keep flat and store in a cool, dry place
- Do not expose to UV rays as material will become brittle
- Shelf life in sealed packaging is 12 months
- In cold weather, application will be assisted by storing overnight at room temperature

## STANDARDS

**GripRoll** is BBA HAPAS Approved.

## SAFETY

### SAFETY HANDLING PRECAUTIONS (when hot)

- Wear suitable protective clothing (heat resistant gauntlet gloves, overalls, protective footwear, face visor)
- DO NOT allow water to contact hot material
- DO NOT exceed maximum safe heating temperature
- If molten material contacts skin:
  - DO NOT attempt to remove
  - Immerse affected area in cold running water for at least 10 minutes
  - Seek medical advice without delay


For full safety information please request the **GripRoll** Safety Data Sheet 164 using the contact information at the back of this brochure.



# ANTISKID

Antiskid Sheets	32
Colasgrip	34
Preformed Surface Dressing	37
Tac-Pads	38
Thermosafe 65	40





**Antiskid Sheets** are skid resistant thermoplastic sheets available in a variety of colours which are ideal for application on bus and cycle lanes as well as other high stress areas. **Antiskid Sheets** are easy to use, can be cut to size and are instantly trafficked once cooled. **Antiskid Sheets** are non-toxic, contain no lead or chromate pigments and are skid resistant to >55 SRV.

## PREPARATION

**Antiskid Sheets** are easy to apply to bituminous and concrete surfaces. Before application always ensure the area is clean, dry and free from dust, oil and fuel residues. **Premark Primer** should be used when **Antiskid Sheets** are applied to concrete, stone and worn macadam surfaces. Ensure that the primer is completely dry before the material is applied. In cold conditions warming the surface prior to application is required to enhance adhesion.

## APPLICATION

**Antiskid sheets** should be placed on the surface with the beaded top coat facing up making sure the individual pieces are positioned correctly and with no gaps in-between.

The material should be heated using a powerful gas burner (pressure min. 3 bar). Move the flame slowly but steadily 10-30cm over the material in a sweeping motion so that heat is evenly applied. The material must be heated until all the material is liquid (approx. 200°C).

If enhanced skid resistance is required calcined bauxite should be applied using a shovel as soon as the **Antiskid Sheet** material is molten and, working in small areas (approximately

200mm) at a time, ensure that it has embedded into the melted **Antiskid Sheet**. Repeat the process until the **Antiskid Sheet** is completely covered.

Once cooled the excess bauxite should then be removed using a stiff brush, with any areas where bauxite has not been retained being reheated and further bauxite applied.

Applying insufficient heat to the **Antiskid Sheets** will result in inadequate bonding and subsequent failure of the material. If overheated, superficial scorching of the material can occur resulting in brown blotching, but this discolouring will soon disappear once the **Antiskid Sheets** are exposed to traffic and weather.

## COVERAGE

Each sheet will cover an area of 1m x 600mm. 1 x 25kg bag of 1-3mm calcined bauxite is sufficient to treat three **Antiskid Sheets**.

## PACKAGING

**Antiskid Sheets** are supplied in flat pack boxes each box contains 5 sheets (1000mm x 600mm).

## STORAGE

- Keep flat and store in a cool, dry place - between 2°C and 32°C
- Maximum of 25 packs high
- Shelf life in sealed packaging is 12 months
- In cold weather, application will be assisted by storing overnight at room temperature

## STANDARDS

Complies to EN 1436 Classes: S3, Q3, R3.

## SAFETY

SAFETY HANDLING PRECAUTIONS (when hot)

- Wear suitable protective clothing (heat resistant gauntlet gloves, overalls, protective footwear, face visor)
- DO NOT allow water to contact hot material
- DO NOT exceed maximum safe heating temperature
- If molten material contacts skin:
  - DO NOT attempt to remove
  - Immerse affected area in cold running water for at least 10 minutes
  - Seek medical advice without delay

For full safety information, please request the **Antiskid Sheet** Safety Data Sheet 106 using the contact information at the back of this brochure.



**Colasgrip** is a high performance, high friction coloured surface treatment. It comprises of a two component thermosetting pigmentable epoxy resin binder dressed with natural or pigmented coloured aggregates, normally calcined bauxite or granite. **Colasgrip** is a chemically curing system and can also be used for protection against fuel or oil spillage and de-icing salts.

## WHERE TO USE?

- Carriageways (especially junctions, bends, roundabouts and other hazard areas)
- Bus lanes
- Cycle lanes
- Pedestrian crossings
- Heritage/decorative
- Rumble strips
- Toll approaches

## PREPARATION

Prior to application of **Colasgrip**, ensure that surfaces are clean, sound and dry.

All dust, dirt and loose material should be swept from the surface.

If the surface is dirty or contaminated by oil or grease, it should be water jet washed or cleaned using a 2% aqueous solution of detergent applied over the whole surface. The surface should then be scrubbed vigorously with a stiff brush to remove contaminants, thoroughly washed with clean water and allowed to dry or dried with a hot compressed air lance.

Any damage to the surface or irregularity must be repaired properly before applying **Colasgrip**.

New asphalt should be trafficked for at least four weeks before applying **Colasgrip**.

**Colasgrip** should not be applied to “fatted up” black top or multi-layer surface dressings.

Ensure surface is completely dry and above 5°C.

If necessary the texture depth of the surface should be studied and measured to determine the consumption rate of the binder. Measurement should be carried out using the sand patch method.

## MIXING

1. The A and B components (resin and hardener) may separate in the containers on storage. It is essential that each component is stirred using the low speed high torque drill fitted with helical stirrer for 2 minutes and re-dispersed properly before mixing together. Component A should be stirred first ensuring that the stirrer is cleaned before stirring component B.
2. If coloured binder is required 1 sachet of pigment should be added to component B and mixed for 2 minutes until it is a uniform colour.
3. Empty the contents of the smaller container (component A) into the larger container (component B) for mixing and blending.
4. Mix contents together using the low speed high torque drill fitted with helical stirrer. Advised duration of mixing process is two minutes. It is essential that all of the component from each container are mixed thoroughly with the other component. Ensure material from the bottom, sides and corners is mixed properly. Failure to mix the binder properly will result in poor strength and cure of the system.
5. In cold weather, store the binder overnight in a warm store. This lowers the viscosity of the binder and makes it easier to use. It may also be necessary to pre-warm the A and B components to 20°C to help pouring and blending.



## APPLICATION

**Colasgrip** is ideal for the delineation of bus and cycle lanes, pedestrian crossings, junctions, bends, roundabouts and other hazard areas. For each type of application Colas can recommend the right type and size of aggregate to use.

Place the aggregate to one side.

The temperature of A & B components should be between 10°C and 35°C before mixing, with the ambient temperature range being between 5°C and 35°C.

The mixed binder should be poured out as uniformly as possible and distributed by squeegee with serrated edge ('V' notches) 5mm wide and 5mm deep at 5mm centres. Care should be taken to obtain an even coating without puddles or thinly spread areas. Application rate will depend on texture depth and will be between 1.3-2.0kg/m<sup>2</sup>.

Once satisfied that there is an even coating of the binder without puddles or thinly spread areas the aggregate should be applied as soon as possible. Bags of aggregate should be distributed along the length of the area to be covered to aid this application. As the epoxy resin is applied the bags are split and the aggregate applied onto the binder to excess. The aggregate should be “broadcast” onto the surface and where necessary a soft brush or flat bladed squeegee can be used to gently even the distribution. Rolling is not required. Using 1-3mm aggregate the application rate is 10-12kg/m<sup>2</sup>.

After all of the areas have been covered with aggregate to excess, the material must

be allowed to cure. The time it will take the material to cure will vary according to the surface temperature, but is typically 2 hours at 25°C. After completion the area should be swept to remove excess aggregate to leave around 6-10kg/m<sup>2</sup> of aggregate on the surface. The excess aggregate may be collected and used again as long as it has not been contaminated.

Use **Leoclean** cleaning fluid to clean the equipment before the mixed material has hardened.

## EQUIPMENT

The equipment required for the hand application of **Colasgrip** is generally composed of:

- 1 stirrer (low speed high torque drill fitted with helical stirrer)
- Serrated 'V' notched squeegees
- Mobile generator
- Mixing container
- Soft and stiff bristle brushes
- Shovel

Other optional equipment such as a mechanical sweeper with suction system and heating tanks may be required but this will depend on the size of the site(s).

## COVERAGE

Binder: 1.4-2.2kg/m<sup>2</sup> (dependant on surface texture)

Aggregate: 10-12kg/m<sup>2</sup> (minimum 6-10kg/m<sup>2</sup> after sweeping)

## PACKAGING

**Colasgrip** is supplied in premeasured kits containing sufficient binder and aggregate to treat approximately 5 or 16m<sup>2</sup> (subject to surface texture of substrate).

## STORAGE

12 months if stored in dry conditions, under cover, above 10°C and out of direct sunlight.



## STANDARDS

**Colasgrip** is produced to a manufacturing system accredited to ISO9001.

## SAFETY

For full safety information, please request the **Colasgrip** Safety Data Sheet 128C and 129C using the contact information at the back of this brochure.



**Prefomed Surface Dressing** is an exceptionally versatile, ready-to use, hard wearing skid resistant surface for pedestrian trafficked areas. **Prefomed Surfacing Dressing** comprises a high performance polymer modified bituminous binder and a layer of skid resistant calcined bauxite chippings strengthened by an integral mesh. **Prefomed Surface Dressing** can be used on most surfaces, including wood, concrete, asphalt and steel.

## WHERE TO USE?

- Footways
- Foot-ramps
- Footbridges
- Platforms
- Pedestrian subways

## PREPARATION

Surfaces must be dry, clean and free from dust, oil and fuel spillage. **CP Primer** should be used to enhance initial adhesion of **Prefomed Surface Dressing** on all sites.

## APPLICATION

Roll out enough material to cover the area to be surfaced and with the backing film upwards cut the **Prefomed Surface Dressing** with a sharp knife. Then prime the substrate using **CP Primer** applying as thinly and evenly as possible as too much could result in the primer bleeding through or the debonding of the **Prefomed Surface Dressing**.

When the **CP Primer** is touch dry, peel off the backing film and apply the **Prefomed Surface Dressing** to the surface. Take care to ensure that the positioning of the **Prefomed Surface Dressing** is accurate as once laid it is extremely difficult to remove. Edges should be butt jointed or overlapped to achieve a neat close-fitting finish.

## COVERAGE

Each roll will cover 5m<sup>2</sup>.

## PACKAGING

**Prefomed Surface Dressing** is supplied in rolls 5m long by 1m wide, 30 rolls per pallet.

## STORAGE

Rolls should be stored upright. Keep in dry store under cover and protect from frost and extreme heat.

## STANDARDS

**Prefomed Surface Dressing** is produced to a manufacturing system accredited to ISO9001.

## SAFETY

For full safety information, please request the **Prefomed Surface Dressing** Safety Data 14 using the contact information at the back of this brochure.



**Tac-Pads** are a two part system and are installed to alert blind and partially sighted people to proceed with caution. **Tac-Pads** are easy to apply, can be trafficked immediately and are available in red, buff or grey. **Tac-Pads** are non-toxic, contain no lead or chromate pigments and are skid resistant to >55 SRV.

## WHERE TO USE?

- Footpaths
- Uncontrolled crossing points
- Controlled crossing points
- Cycle routes
- Approach to any hazardous areas

## PREPARATION

**Tac-Pads** must be applied to a level surface. **Premark Primer** is required for concrete, stone and worn macadam surfaces.

Clean application area thoroughly by removing all sand, dirt, chemicals and oily substances. Remove all moisture present (if any) in the surface with a gas burner.

## APPLICATION

Place both adhesive and **Tac-Pad** layers in position ensuring that the beaded side of the **Tac-Pad** sheet is uppermost and that the individual pieces are positioned correctly and with no gaps in-between. Sheets may be cut to shape using tinsnips or a stanley knife if required.

Remove the **Tac-Pad** layer and heat the adhesive layer using a powerful gas burner (pressure min. 3 bar). Move the flame slowly but steadily 10cm to 30 cm over the material in a sweeping motion so that heat is evenly applied. The material must be heated until all the material is liquid (approx. 200°C). Immediately after heating place the **Tac-Pad** on top of the adhesive layer with the beaded top coat facing up.

Applying insufficient heat will result in inadequate bonding and failure. If overheated, superficial scorching of the material can occur resulting in brown blotching, but this discolouring will soon disappear once the marking is exposed to traffic and weather.

For application on non-bituminous surface (e.g. concrete) follow the same steps as above but in addition apply **Premark Primer** (sealer) to the entire surface area where the **Tac-Pads** are to be installed. Allow the primer to dry until it is no longer sticky before applying the **Tac-Pads**.

Follow steps in the first paragraph above.

Apply **Premark Primer** (sealer) on to the entire surface area where the marking is to be installed. Allow the primer to dry until it is no longer sticky. The more porous the surface, the more primer is required.

## COVERAGE

Both the **Tac-Pad** and adhesive layer are 400mm x 400mm.

## PACKAGING

**Tac-Pads** are supplied in flat pack cardboard boxes each box contains 10 sets.



## STORAGE

- Keep flat and store in a cool, dry place between 2°C and 32°C
- Maximum of 25 packs high
- Shelf life in sealed packaging is 12 months
- In cold weather, application will be assisted by storing overnight at room temperature

## STANDARDS

Complies to EN 1436 Classes: S3, Q3, R3.

## SAFETY

SAFETY HANDLING PRECAUTIONS (when hot)

- Wear suitable protective clothing (heat resistant gauntlet gloves, overalls, protective footwear, face visor)
- DO NOT allow water to contact hot material
- DO NOT exceed maximum safe heating temperature
- If molten material contacts skin:
  - DO NOT attempt to remove
  - Immerse affected area in cold running water for at least 10 minutes
  - Seek medical advice without delay

For full safety information, please request the **Tac Pads** Safety Data Sheet 106 using the contact information at the back of this brochure.

# THERMOSAFE 65



**Thermosafe 65** is a skid resistant thermoplastic sheet for surfaces that require a higher skid resistant finish. Available in a variety of colours, **Thermosafe 65** are ideal for worn /polished road surface covers and to provide a non-slip surface to stairs, steps and access ramps for the disabled.

**Thermosafe 65** is cost effective and a rapid effective solution to those road users most at risk, i.e. those who ride motorcycles or scooters and are particularly vulnerable to sudden changes in surface grip. The sheets are easy to use; can be cut to size and are instantly trafficked once cooled. **Thermosafe 65** is non-toxic, contain no lead or chromate pigments and is skid resistant to >65 SRV.

## WHERE TO USE?

- Footpaths
- Uncontrolled crossing points

## PREPARATION

**Thermosafe 65** is easy to apply to ironwork, bituminous, concrete, block paving as well as treated and untreated surfaces. Always ensure the area is clean, dry and free from dust, oil and fuel residues. Warming the surface prior to application is required to enhance adhesion. Apply **Thermosafe Primer** to the area and apply the sheets immediately.

## APPLICATION

**Thermosafe 65** should be applied with a hand lance. Trafficking can commence when material has fully cooled. Sheets may be cut to shape using tinsnips or a Stanley knife if required.

## COVERAGE

Each sheet will cover an area of 1000mm x 600mm.

## PACKAGING

**Thermosafe 65** is supplied in flat pack cardboard boxes, each box contains 5 sheets (1000mm x 600mm).

## STORAGE

- Keep flat and store in a cool, dry place - between 2°C and 32°C
- Maximum of 25 packs high
- Shelf life in sealed packaging is 12 months
- In cold weather, application will be assisted by storing overnight at room temperature

## STANDARDS

Complies to EN 1436 Classes: S5.

## SAFETY

### SAFETY HANDLING PRECAUTIONS (when hot)


- Wear suitable protective clothing (heat resistant gauntlet gloves, overalls and protective footwear)
- DO NOT allow water to contact hot material
- DO NOT exceed maximum safe heating temperature
- If molten material contacts skin:
  - DO NOT attempt to remove
  - Immerse affected area in cold running water for at least 10 minutes
  - Seek medical advice without delay

For full safety information, please request the **Thermosafe 65** Safety Data Sheet 106 using the contact information at the back of this brochure.



# SEALANTS

C-Joint	42
Jointfill N1	43
Coljoint N2	45
Jointfill A2	47
Sett Grout	49
Stud Grout	50



Problems with bridge expansion joints are well known. A punishing environment created by traffic loads and climate conditions means that the right jointing system is imperative if the structure and bearings are to be protected from water and salts.

Expansion joint systems developed in the past have either not performed adequately, e.g. due to mechanical failure, or were not cost effective. **C-Joint** bridges this gap.

**C-Joint** is the perfect choice of system for low to medium movement bridge expansion joints. It is an asphaltic plug joint which is able to accommodate up to  $\pm 25$ mm horizontal movement from mid gap opening position. Special grades are designed for greater movement for particular situations.

The main components of **C-Joint** are a high performance elastomer modified bitumen binder and single size aggregate. Together they create a joint matrix which gives both flexibility and strength enabling the joint to accommodate all kinds of movement whether they are thermal, rotational or traffic induced. As it is completely watertight the bridge structure and bearing system are fully protected.

Several different grades of binder are available in order to meet different climatic conditions throughout the world. For the bridge engineer **C-Joint** is a cost effective, durable and versatile bridge joint system and comes with the guarantee of the Colas name.

## FEATURES AND BENEFITS

### FLEXIBLE

**C-Joint** is virtually omni-directional being able to accommodate longitudinal, rotational, vertical and transverse movements. It can accommodate up to  $\pm 25$ mm horizontal movement.

### WATERTIGHT

Being completely watertight, **C-Joint** protects the structure and bearing system from moisture. Drainage can be incorporated into **C-Joint** to remove any sub surface water.

### SILENT

When trafficked there is little or no increase in noise levels.

### QUICK INSTALLATION

Rapid installation and the ability to be installed in partial widths reduces the disruption to road users and other costs.

### VERSATILE AND ADAPTABLE

**C-Joint** can be installed in new and old structures and is constructed to meet the requirements of individual sites.

### RAPIDLY AND EASILY REPAIRED

If damaged by accident, **C-Joint** can be easily and rapidly repaired. During resurfacing work it can be planed off and topped up again.

### SAFE

**C-Joint** is flush with the road surface, provides no obstacle to traffic and has no parts to come loose and become traffic hazards.

### DURABLE

**C-Joint** contains no mechanical parts which may require replacement and is able to withstand structure movements and traffic loads in all climates.

## SAFETY

### SAFETY HANDLING PRECAUTIONS (when hot)

- Wear suitable protective clothing (heat resistant gauntlet glove, overalls, protective footwear, face visor).
- DO NOT allow water to contact hot material.
- DO NOT exceed maximum safe heating temperature.
- If molten material contacts skin:
  - DO NOT attempt to remove.
  - Immerse affected area in cold running water for at least 10 minutes.
  - Seek medical advice without delay.

This product is hazardous for transportation when carried at temperatures above 100°C.

For full safety information, please request the **C-Joint** Safety Data Sheet 91 using the contact information at the back of this brochure.

## COVERAGE

Weight of Jointfill N1 Sealant to fill 100m joint (kg)						
Depth of joint (mm)	Width of joint (mm)					
	15	20	25	30	35	40
20	35	46	58	70	81	93
25	-	-	72	87	101	116
30	-	-	-	-	122	139
35	-	-	-	-	142	162
40	-	-	-	-	-	185

## PACKAGING

**Jointfill N1** is available in plastic lined papersacks holding 15kg (nominal). Remove the paper and load into heating equipment.

## STORAGE

Keep in dry store under cover.

## STANDARDS

**Jointfill N1** is manufactured on a purpose-built plant to an ISO 9001 quality system which covers all Colas manufactured products. Under this system all batches undergo rigorous QC testing before being released for use. **Jointfill N1** complies with the specification given BS EN14188-1:2004 Joint Fillers and Sealants - specifications for hot applied sealants for a Type N1 Sealant.

**Jointfill N1** is a polymer modified, bituminous, hot applied joint sealant compound. It is designed to be tough, flexible and have good extension properties over a wide range of ambient temperatures. **Jointfill N1** is suitable for joints between concrete and bituminous surfacing preventing entry of water and other materials. It has excellent recovery properties and low temperature flexibility.

**Jointfill N1** is not recommended for overbanding due to its lack of skid resistance. **Jointgrip OB** is recommended for overbanding due to its superior skid resistance properties.

## WHERE TO USE?

- Carriageways
- Runways
- Motorways
- Footways

## PREPARATION

Damaged joints must be repaired using an epoxy mortar approved by Colas. If necessary joints should also be treated by grit blasting. Joints and cracks should always be thoroughly cleaned and dried with a hot compressed air lance in order to remove all moisture and dirt. This process should be carried out immediately prior to the application of **Jointfill N1**.

Concrete joints should be primed with **CP Primer** before applying **Jointfill N1**.

## APPLICATION

**Jointfill N1** should be heated indirectly and agitated in a purpose-built sealant preheater unit with thermostatic control. Ensuring that the temperature does not exceed 190°C. The heater unit should be air-jacketed or oil-jacketed. The materials should then be pumped in to the joint, or poured at temperatures between 170-190°C using a melter pourer or bucket with a 'V' lip, with the minimum loss of temperature. Joints should be sealed to a level of at least 3mm below the surface.

Application Properties	
Pouring temperature	170°C - 190°C
Safe heating temperature	185°C for 6 hours maximum. 190°C maximum temperature

Test Name	Method	Specification
Softening point (Ring and Ball)	BS EN 1427	≥85 °C
Cone penetration (25°C, 150g, 5s)	BS EN 13880-2	40 to 130dmm
Resilience (25°C, 75g ball, 5s)	BS EN 13880-3	≥60%
Flow resistance (60°C, 5h, 75%)	BS EN 13880-5	<2mm
Extension test: 3 cycles of extension to 75% at a rate of 6mm/hr @ -20°C	BS EN 13880-10	Pass 3 cycles
Density	BS EN 13880-1	Typically 1.015g/cm <sup>3</sup> @ 25°C

## SAFETY

### SAFETY HANDLING PRECAUTIONS (when hot)

- Wear suitable protective clothing (heat resistant gauntlet glove, overalls, protective footwear, face visor).
- DO NOT allow water to contact hot material.
- DO NOT exceed maximum safe heating temperature.
- If molten material contacts skin:
  - DO NOT attempt to remove.
  - Immerse affected area in cold running water for at least 10 minutes.
  - Seek medical advice without delay.

This product is hazardous for transportation when carried at temperatures above 100°C.

For full safety information, please request the **Jointfill N1** Safety Data Sheet 06 using the contact information at the back of this brochure.

**Coljoint N2** is a polymer modified, bituminous, hot applied joint sealant compound. It is designed to be tough, flexible and have good extension properties over a wide range of ambient temperatures.

**Coljoint N2** is suitable for joints between concrete and bituminous surfacing preventing entry of water and other materials. It has excellent recovery properties and low temperature flexibility.

**Coljoint N2** is not recommended for overbanding due to its lack of skid resistance. **Jointgrip OB** is recommended for overbanding due to its superior skid resistance properties.

## WHERE TO USE?

- Carriageways
- Runways
- Motorways
- Footways

## PREPARATION

Damaged joints must be repaired using an epoxy mortar approved by Colas. If necessary joints should also be treated by grit blasting. Joints and cracks should always be thoroughly cleaned and dried with a hot compressed air lance in order to remove all moisture and dirt. This process should be carried out immediately prior to the application of **Coljoint N2**.

Concrete joints should be primed with **CP Primer** before applying **Coljoint N2**.

## APPLICATION

**Coljoint N2** should be heated indirectly and agitated in a purpose-built sealant preheater unit with thermostatic control. Ensuring that the temperature does not exceed 195°C. The heater unit should be air-jacketed or oil-jacketed. The materials should then be pumped in to the joint, or poured at temperatures between 175–190°C using a melter pourer or bucket with a 'V' lip, with the minimum loss of temperature. Joints should be sealed to a level of at least 3mm below the surface.

Application Properties	
Pouring temperature	170°C - 190°C
Safe heating temperature	185°C for 6 hours maximum. 190°C maximum temperature

## COVERAGE

Weight of Coljoint N2 Sealant to fill 100m joint (kg)						
Depth of joint (mm)	Width of joint (mm)					
	15	20	25	30	35	40
20	30	40	50	60	70	80
25	-	-	62.5	75	87.5	100
30	-	-	-	90	105	120
35	-	-	-	-	122.5	140
40	-	-	-	-	-	160

## PACKAGING

**Coljoint N2** is available in plastic lined papersacks holding 15kg (nominal). Remove the paper leaving plastic liner and load into heating equipment.

## STORAGE

Keep in dry store under cover.

## STANDARDS

**Coljoint N2** complies with the specification given in BS 2499: Part 1 1993 Hot-applied joint sealant systems for concrete pavements - Part 1. Specifications for Joint Sealants; Type N2 Sealant.

## COLJOINT N2

Test Name	Specification
Cone Penetration (25°C, 150g)	4 to 10mm
Flow (60°C, plate)	<10mm
Extension Test (3 cycles at -20°C at 6mm/hour for 3 hours)	<50mm <sup>2</sup> debonding <20mm <sup>2</sup> rupture, with less than 3mm depth Force between 160-1600N
Resilience (25°C)	40% minimum recovery
Determination of bitumen compatibility	No adhesion failure, no oily exudate
Softening Point	≥85°C
Density at 25°C (g/cm <sup>3</sup> )	1.017 (Typical value)

## SAFETY

## SAFETY HANDLING PRECAUTIONS (when hot)

- Wear suitable protective clothing (heat resistant gauntlet glove, overalls, protective footwear, face visor).
- DO NOT allow water to contact hot material.
- DO NOT exceed maximum safe heating temperature.
- If molten material contacts skin:
  - DO NOT attempt to remove.
  - Immerse affected area in cold running water for at least 10 minutes.
  - Seek medical advice without delay.

This product is hazardous for transportation when carried at temperatures above 100°C.

For full safety information, please request the **Coljoint N2** Safety Data Sheet 06 using the contact information at the back of this brochure.

## JOINTFILL A2

Application Properties	
Pouring temperature	170°C/190°C
Safe heating temperature	185°C for 6 hours maximum. 190°C maximum temperature

## COVERAGE

Weight of Jointfill A2 Sealant to fill 100m joint (kg)						
Depth of joint (mm)	Width of joint (mm)					
	15	20	25	30	35	40
20	36	48	60	72	84	96
25	-	-	75	90	105	120
30	-	-	-	108	126	144
35	-	-	-	-	147	168
40	-	-	-	-	-	192

## PACKAGING

**Jointfill A2** is supplied in plastic lined paper sacks holding 20kg (nominal) of material. Remove paper and put in to heating equipment.

## STORAGE

Keep in dry store under cover.

## STANDARDS

**Jointfill A2** is manufactured on a purpose-built plant to an ISO 9001 quality system which covers all Colas manufactured products. Under this system all batches undergo rigorous QC testing before being released for use. If a BS EN14188-1:2004 product is required see **Jointfill N1**.

**Jointfill A2** is a hot applied rubberised bitumen compound designed to be tough, flexible and have good extension properties over a wide range of temperature conditions. It is used for sealing horizontal expansion joints on concrete and asphalt pavements where low movement is expected.

**Jointfill A2** prevents entry of water and other materials, it has good recovery properties and low temperature flexibility. **Jointfill A2** is not recommended for overbanding due to its lack of skid resistance, **Jointgrip OB** is recommended for this application due to its superior skid resistance properties.

## WHERE TO USE?

- Carriageways
- Car parks
- Footways

## PREPARATION

Damaged joints must be repaired using an epoxy mortar approved by Colas. If necessary joints should also be treated by grit blasting. Joints and cracks should always be thoroughly cleaned and dried with a hot compressed air lance in order to remove all moisture and dirt. This process should be carried out immediately prior to the application of **Jointfill A2**. Concrete joints should be primed with **CP Primer** before applying **Jointfill A2**.

## APPLICATION

**Jointfill A2** should be heated indirectly and agitated in a purpose-built sealant preheater unit with thermostatic control. Ensuring that the temperature does not exceed 190°C. The heater unit should be air-jacketed or oil-jacketed. The materials should then be pumped in to the joint, or poured at temperatures between 170-190°C using a melter pourer or bucket with a 'V' lip, with the minimum loss of temperature. Joints should be sealed to a level of at least 3mm below the surface.

More thorough advice is given in BS2499-2:1992 Hot Applied Joint Sealant Systems for Concrete Pavements. Code of Practice for Application and Use of Joint Sealants.



Test Name	Specification
Softening point (Ring and Ball)	Typically 70 - 90°C
Cone penetration (25°C, 150g)	25 - 50mm
Flow resistance (Mould Method at 45°C)	<15%
Extension test (0°C, ASTM D1191)	Pass 3 cycles
Density	Typically 1.2g/cm <sup>3</sup> at 25°C

## SAFETY

### SAFETY HANDLING PRECAUTIONS (when hot)

- Wear suitable protective clothing (heat resistant gauntlet glove, overalls, protective footwear, face visor).
- DO NOT allow water to contact hot material.
- DO NOT exceed maximum safe heating temperature.
- If molten material contacts skin:
  - DO NOT attempt to remove.
  - Immerse affected area in cold running water for at least 10 minutes.
  - Seek medical advice without delay.

This product is hazardous for transportation when carried at temperatures above 100°C.

For full safety information, please request the **Jointfill A2** Safety Data Sheet 06 using the contact information at the back of this brochure.



**Sett Grout** is a hot applied bituminous compound which secures all types of setts/ cobbles. **Sett Grout** has been developed in order to solve the pouring and setting problems encountered with some filled bitumen grouting materials. Adhesion, flow and pouring properties have been improved whilst still retaining recommended softening point and penetration characteristics.

## WHERE TO USE?

- To secure all types of setts and cobbles

## PREPARATION

When grouting cobbles/setts, use the cobbles/ setts manufacturer's installation instructions ensuring that cobbles/setts are dry and clean.

## APPLICATION

**Sett Grout** should be heated indirectly and agitated/stirred in a purpose-built sealant preheater-unit with thermostatic control to ensure that solids are evenly dispersed throughout the pouring material at all times. The heater unit should be air-jacketed or oil-jacketed. Ensure that the temperature does not exceed 190°C as this will result in hardening and loss of elasticity. The materials should then be pumped into the joint, or poured at temperatures between 170-180°C using a melter pourer or bucket with a 'V' lip, with the minimum loss of temperature. Joints should be sealed to a level of at least 3mm below the surface. In cold conditions the temperature of the **Sett Grout** should be raised accordingly and in frosty weather this could well be up to, but not above, 190°C to counteract the chilling effect the setts/cobbles will have on the poured grout.

## COVERAGE

The spread rate for a 20mm wide x 75mm deep joint - 3kg/linear metre of joint. N.B: When using 200mm x 100mm setts, 1m<sup>2</sup> of granite setts contains 15 linear metres of joint. On this basis, the spread rate of **Sett Grout** is 45kg/ m<sup>2</sup> of granite setts, assuming joints are 20mm wide x 75mm deep.

## PACKAGING

**Sett Grout** is available in 25kg (nominal) paper sacks or as a shrink-wrapped pallet (40 x 25kg).

## STORAGE

Keep in dry store under cover.

## STANDARDS

**Sett Grout** is a proprietary product produced to a manufacturing system accredited to ISO9001.

## SAFETY

### SAFETY HANDLING PRECAUTIONS (when hot)

- Wear suitable protective clothing (heat resistant gauntlet glove, overalls, protective footwear, face visor).
- DO NOT allow water to contact hot material.
- DO NOT exceed maximum safe heating temperature.
- If molten material contacts skin:
  - DO NOT attempt to remove.
  - Immerse affected area in cold running water for at least 10 minutes.
  - Seek medical advice without delay.

This product is hazardous for transportation when carried at temperatures above 100°C.

For full safety information, please request the **Sett Grout** Safety Data Sheet 33 using the contact information at the back of this brochure.

# STUD GROUT



**Stud Grout** is a hot applied bituminous compound which secures reflective road studs.

**Stud Grout** has been developed in order to solve the pouring and setting problems encountered with some bitumen grouting materials. Adhesion, flow and pouring properties have been improved whilst still retaining recommended softening point and penetration characteristics.

## WHERE TO USE?

- To secure all types of reflective road studs

## PREPARATION

When grouting road studs, use the road stud manufacturer's installation instructions ensuring that studs are dry and clean.

## APPLICATION

**Stud Grout** should be heated indirectly and agitated/stirred in a purpose-built sealant preheater-unit with thermostatic control to ensure that solids are evenly dispersed throughout the pouring material at all times. The heater unit should be air-jacketed or oil-jacketed. Ensure that the temperature does not exceed 190°C as this will result in hardening and loss of elasticity. The materials should then be pumped into the joint, or poured at temperatures between 170-180°C using a melter pourer or bucket with a 'V' lip, with the minimum loss of temperature. Joints should be sealed to a level of at least 3mm below the surface. In cold conditions the temperature of the **Stud Grout** should be raised accordingly and in frosty weather this could well be up to, but not above, 190°C to counteract the chilling effect the stud will have on the poured grout.

## COVERAGE

Spread Rate - refer to road stud manufacturer's guidance.

## PACKAGING

**Stud Grout** is available in 25kg (nominal) paper sacks or as a shrink-wrapped pallet (40 x 25kg).

## STORAGE

Keep in dry store under cover.

## STANDARDS

**Stud Grout** is a proprietary product produced to a manufacturing system accredited to ISO9001.

## SAFETY

### SAFETY HANDLING PRECAUTIONS (when hot)

- Wear suitable protective clothing (heat resistant gauntlet glove, overalls, protective footwear, face visor).
- DO NOT allow water to contact hot material.
- DO NOT exceed maximum safe heating temperature.
- If molten material contacts skin:
  - DO NOT attempt to remove.
  - Immerse affected area in cold running water for at least 10 minutes.
  - Seek medical advice without delay.

This product is hazardous for transportation when carried at temperatures above 100°C.

For full safety information, please request the **Stud Grout** Safety Data Sheet 33 using the contact information at the back of this brochure.



# FOOTWAY SURFACE TREATMENTS

Cationic Slurry Seal Emulsion	52
Leocatic Spray	54
Leochip VLS	56

## CATIONIC SLURRY SEAL EMULSION (CSS)

## CATIONIC SLURRY SEAL EMULSION (CSS)



**Cationic Slurry Seal Emulsion (CSS)** is a key constituent of slurry seal for hand or machine application. Ideal for rejuvenating cracked, spalled and worn surfaces.

**CSS** is based on a K3 cold emulsion with a fast application and drying time of approximately 30 minutes. This means that the material can be laid quickly, economically and safely with the minimum disruption to road users and residents.

By varying the size of aggregates used, the texture depth can be altered to suit site requirements with typical slurries based on 0/4 or 0/6mm grades for footway or urban carriageway application.

Other components are required to be mixed on site with **CSS** emulsion in order to produce a slurry seal e.g. stabiliser, cellulose fibre and cement. These materials are supplied by Colas and further details are available on request.

For higher stressed areas, Colas Ltd can offer a polymer modified version of **CSS**, please contact our National Sales Office for further information.

### WHERE TO USE?

- Footways
- Carriageways
- Car parks
- Hard shoulders

### PREPARATION

The surface to be treated must be free from all dust and loose material and should be cleaned thoroughly with a mechanical broom and/or suction sweeper, supplemented if necessary by hand sweeping. Open cracks must be cleared of vegetation and other loose material. All debris and loose material arising must be removed.

### APPLICATION

**CSS** emulsion mixes can be produced in simple bell mixers or for larger quantities, in purpose built mixing equipment provided proper attention is given to mix composition. **CSS** mixes are spread using a rubber bladed squeegee and soft broom. It is recommended that **CSS** is only applied when the ground temperature is 5°C and rising or less than 40°C.

### COVERAGE

When using 4mm aggregate the coverage from a 200kg drum is approximately 160–200m<sup>2</sup>.

### PACKAGING

**CSS** is supplied in bulk and in 200kg drums.

### STORAGE

Protect from frost. Drums should be rolled frequently to avoid separation. Bulk material should be circulated before use. For further information please refer to BS434-2:2006, Section 5 Clause 5.2 Storage.

### STANDARDS

**CSS** is a CE Marked cationic emulsion to BS EN13808:2013 C55B(F) or C60B(F).

**CSS** also complies with the withdrawn BS434-1 Standard as a K3 Type emulsion.

Full CE Marking information is available from the Colas Products website.

[www.colasproducts.co.uk](http://www.colasproducts.co.uk)

### PROPERTIES

Particle charge	Positive (Cationic)
Residue on sieving 500Qm	0.1% m/m max
Residue on sieving 160Qm	0.25% m/m max
Binder content	56% m/m min
Efflux 2mm @ 40°C	15-70s (Class3)
Coagulation at low temperature	Nil

### SAFETY

For full safety information, please request the **Cationic Slurry Seal Emulsion** Safety Data Sheet 02S using the contact information at the back of this brochure.

# LEOCATIC SPRAY



**Leocatic Spray** is a 60% Bitumen content, cold applied cationic emulsion. **Leocatic Spray** is particularly useful for the construction and maintenance of footways and other low stress sites. **Leocatic Spray** is an exceptionally versatile product with a variety of uses.

## WHERE TO USE?

- Surface dressing
- Stabilising footpaths
- Patching
- Bond coat

## PREPARATION

Varies depending on the application.

## APPLICATION

### SURFACE DRESSING:

**Leocatic Spray** is ideal for surface dressing lightly trafficked sites such as footways. Depending on site conditions it may be necessary to apply a double surface dressing wherein two binder and chipping applications are carried out in quick succession. Typical rates of application when 6mm chippings are used (as guide only).

### DOUBLE DRESSING

1st application: 0.9-1.4 l/m<sup>2</sup>  
2nd application: 0.9-1.4 l/m<sup>2</sup>  
For design guidelines refer to Road Note 39.

### STABILISING FOOTPATHS:

On sites subject to low stress it may be economical to prepare, in situ, a combined

binder/surface course by means of an application of **Leocatic Spray** into the interstices of the aggregate after the latter has been spread on the foundation and compacted. **Leocatic Spray** is particularly effective where the stone layer is open or wet. For full specification please contact your local Colas office.

### PATCHING:

When repairing potholes and deep depressions, the area to be treated should first be cleaned of all loose material and cut out to a regular shape with all the sides vertical or slightly undercut. The bottom and sides of the hole or depression should be thoroughly coated with emulsion. Clean aggregate should be placed in the hole to a thickness slightly greater than its depth and well rammed or rolled. The minimum amount of emulsion required to coat the stones should then be poured on (excessive amounts of emulsion may create 'fat' spots in the road). The patch should then be covered with clean 10mm or 6mm chippings and again rolled or rammed.

### BOND COAT:

Where coated macadams or asphalts are employed, a bond/tack coat of **Leocatic Spray** can be used (and may be specified) between layers to provide an adhesive and dust free surface.

Typical emulsion rates of application: 0.3-0.5 l/m<sup>2</sup>.

### BASE TREATMENT:

A freshly cut or placed formation and/or freshly laid sub-base can be sealed with **Leocatic Spray** in order to preserve moisture equilibrium and so retain volume and strength.

Typical emulsion rates of application: 0.9-1.4 l/m<sup>2</sup>.

### REMEDIAL TREATMENT:

Where the shape of the surface to be healed is satisfactory but a surface is slippery or in danger of imminent break-up, surface dressing with **Leocatic Spray** may be employed as a remedial treatment to seal the surface and/or restore surface texture.

Approximate rates of application when 6mm chippings are used: 1.1-1.5 l/m<sup>2</sup>.

# LEOCATIC SPRAY

## COVERAGE

Please see opposite page for the various applications for guidance.

## PACKAGING

**Leocatic Spray** is available in bulk, 200kg drums and 25kg containers.

## STORAGE

Protect from frost. 200kg and 25kg units should be rolled frequently to avoid separation. Bulk material should be regularly circulated. For further information please refer to BS434-2: 2006 Clause 5.2 Storage.

## STANDARDS

**Leocatic Spray** is a CE Marked cationic emulsion to BS EN13808:2013 C55B3.

**Leocatic Spray** also complies with the withdrawn BS434-1 Standard as a K1-60 Type emulsion.

Full CE Marking information is available from the Colas Products website.  
[www.colasproducts.co.uk](http://www.colasproducts.co.uk)

## SAFETY

For full safety information, please request the **Leocatic Spray** Safety Data Sheet 23LS using the contact information at the back of this brochure.

# LEOCHIP VLS



**Leochip VLS** is a cold applied, durable surface dressing binder. **Leochip VLS** is ideal for producing a high quality, natural and aesthetically pleasing finish to drives and footpaths.

## WHERE TO USE?

- Driveways
- Footpaths
- Tow paths
- Decorative areas

## PREPARATION

Surfaces must be free from weeds, standing water, dust, dirt, loose material and oil spillage. Any potholes should be patched and any cracks should be filled with Colas **Leoseal R** or a **Leoseal R** and sand mortar mixture.

## APPLICATION

**Leochip VLS** can be poured from a watering can, spread by hand using an ordinary notched rubber bladed squeegee or sprayed through a specially adapted nozzle.

**Leochip VLS** should be applied at a spread rate of 1.3 to 1.8lbs/m<sup>2</sup> depending upon the texture and porosity of the surface and choice of chipping size. Chippings should comply with BS EN 13043 and the recommendations in Table 4 of PD 6682-2. 2.8/6.3mm chippings are recommended.

**Leochip VLS** should be applied in temperatures >10°C and dry conditions should prevail for at least 12 hours after application.

N.B: Not all aggregates are suitable for use with Bitumen Emulsion and advice regarding aggregate suitability can be obtained by contacting our National Sales Office.

## COVERAGE

Depending on the texture and porosity of the surface to be treated **Leochip VLS** will achieve the following approximate coverage rates.

25kg = 14-19m<sup>2</sup>  
 200kg = 110-155m<sup>2</sup>  
 (Typical aggregate coverage is 7-10kg/m<sup>2</sup>)

## PACKAGING

**Leochip VLS** is available in 200kg drums or 25kg containers.

## STORAGE

Protect from frost. Drums should be rolled frequently to avoid separation. For further information please refer to BS434-2:2006. Section 5 Clause 5.2 Storage.

## STANDARDS

Leochip VLS is a CE Marked cationic emulsion to BS EN13808:2013 C67B.

Full CE Marking information is available from the Colas Products website.  
[www.colasproducts.co.uk](http://www.colasproducts.co.uk)

## SAFETY

For full safety information, please request the **Leochip VLS** Safety Data Sheet 23V using the contact information at the back of this brochure.



# SURFACE DRESSING BINDERS

Secure Chip	58
Surfix C	59
Surfix 80S	60
SLX 80	62
Premium 80	64
Prinmuls MP90X	66

# SECURE CHIP



**Secure Chip** is a spray applied emulsion binder for application to recently completed surface dressings.

**Secure Chip** is designed to reduce the amount of post sweeping required by securing the dressing aggregate in the mosaic structure minimising the risk of damaged windscreens from chippings dislodged by passing vehicles. Application of **Secure Chip** also gives a pleasing aesthetic and long lasting black colour resembling an asphalt surface.

The low application rate of **Secure Chip** results in the rapid breaking of the emulsion meaning that sites can be opened to traffic quickly minimising any disruption to local residents.

## WHERE TO USE?

- On recently surface dressed road

## PREPARATION

**Secure Chip** should be applied to recently applied surface dressings that have been swept.

## APPLICATION

**Secure Chip** should be machine spray applied to recent surface dressing, after an initial sweeping of the site, at a temperature of 85°C.

## COVERAGE

**Secure Chip** should be applied at spread rate of 0.2-0.4L/m<sup>2</sup>.

## PACKAGING

**Secure Chip** is supplied in bulk loads.

## STORAGE

**Secure Chip** should be stored at 80-85°C in purpose build bulk storage tanks or spray tankers. For further guidance please contact our National Sales office.

## STANDARDS

**Secure Chip** complies with BS EN 13808:2013 C50BP3/4 or C55BP3/4.

## SAFETY

For full safety information, please request the **Secure Chip** Safety Data Sheet 156S using the contact information at the back of this brochure.

# SURFIX C



**Surfix C** is a conventional grade cationic bitumen emulsion for surface dressing. By using selected emulsifying agents with a suitable emulsion grade penetration bitumen **Surfix C** has been specifically designed for use as a hot applied surface dressing binder.

## WHERE TO USE?

**Surfix C** is suitable for use on carriageways, driveways, footways, canal tow paths and all sites as a conventional grade surface dressing binder as specified in the Design Guide for Road Surface Dressing, Road Note 39.

## PREPARATION

Please refer to the Road Surface Treatment Association's (RSTA)/ADEPT Code of Practice for Surface Dressing Part 5 – Surface Preparation.

## APPLICATION

**Surfix C** should be applied at a temperature of 85°C through a bulk binder distributor which has been tested for compliance to BS 1707 (hot binder distributors for surface dressing).

The surface dressing works should be in accordance with the recommendations contained in Design Guide for Road Surface Dressing, Road Note 39 and the RSTA's Codes of Practice for Surface Dressing.

## COVERAGE

Refer to the Design Guide for Road Surface Dressing, Road Note 39 or contact our National Sales Office using the details at the back of this brochure for further guidance.

## PACKAGING

Supplied in bulk loads and 200kg drums.

## STORAGE

In purpose built bulk storage tanks or spray tankers **Surfix C** should be stored at 80-85°C and circulated daily. Drums should be rolled frequently to avoid separation and must be protected from frost. For further information regarding the storage of emulsion in drums please refer to BS434-2:2006 Clause 5.2 Storage.

## STANDARDS

**Surfix C** is a CE Marked cationic emulsion to BS EN13808:2013 C69BF2/3/4.

**Surfix C** also complies with the withdrawn BS434-1 Standard as a K1-70 Type emulsion.

Full CE Marking information is available from the Colas Products website.

[www.colasproducts.co.uk](http://www.colasproducts.co.uk)

Emulsion	
Binder content (EN 1428)	67-71% (Class 9)
Efflux 4mm @ 40°C (EN 12846-1)	5 - 100 s (Class 5/6)
Water effect on binder adhesion (EN 13614)	≥ 90 (Class 3)
Breaking behaviour (EN 13075-1)	< 110 - 195 (Class 2/3/4)
Recovered Binder	
Penetration @ 25°C (EN1426)	≤ 330 (Class 7)
Softening point (EN 2538)	≥ 35°C (Class 8)
Cohesion by pendulum (EN 13588)	NR

Dangerous regulated substances	NPD
--------------------------------	-----

## SAFETY

For full safety information, please request the **Surfix C** Safety Data Sheet 15 using the contact information at the back of this brochure.

# SURFIX 80S

# SURFIX 80S



**Surfix 80S** is a BBA HAPAS approved intermediate grade polymer modified bitumen emulsion. By using selected emulsifying agents with a suitable emulsion grade penetration bitumen it has been specifically designed for use as a hot applied surface dressing binder.

## WHERE TO USE?

**Surfix 80S** is suitable for use on carriageways, driveways, footways, canal tow paths and all sites as an intermediate grade surface dressing binder as specified in the Design Guide for Road Surface Dressing, Road Note 39.

## PREPARATION

Please refer to the Road Surface Treatment Association's (RSTA)/ADEPT Code of Practice for Surface Dressing Part 5 – Surface Preparation.

## APPLICATION

**Surfix 80S** should be applied at a temperature of 85°C through a bulk binder distributor which has been tested for compliance to BS 1707 (hot binder distributors for surface dressing).

The surface dressing works should be in accordance with the recommendations contained in Design Guide for Road Surface Dressing, Road Note 39 and the RSTA's Codes of Practice for Surface Dressing.

## COVERAGE

Refer to the Design Guide for Road Surface Dressing, Road Note 39 or contact our National Sales Office using the details at the back of this brochure for further guidance.

## PACKAGING

Supplied in bulk loads.

## STORAGE

**Surfix 80S** should be stored at 85°C in a purpose built bulk storage tank or spray tanker and circulated daily. For further information please refer to BS434-2 2006 Clause 5.2 Storage.

## STANDARDS

**Surfix 80S** is a CE Marked cationic bitumen emulsion to BS EN13808:2013 C69BP2/3.

**Surfix 80S** complies with the requirements of Road Note 39, Design Guide for Road Surface Dressing as an Intermediate Grade surface dressing binder.

Full CE Marking information is available from the Colas Products website.  
[www.colasproducts.co.uk](http://www.colasproducts.co.uk)

Emulsion	
Binder content (EN 1428)	67 - 71% (Class 9)
Efflux 4mm @ 40°C (EN 12846-1)	5 - 100 s (Class 5/6)
Water effect on binder adhesion (EN 13614)	≥ 90 (Class 3)
Breaking behaviour (EN 13075-1)	< 110 - 155 (Class 2/3)
Recovered Binder	
Penetration @ 25°C (EN 1426)	≤ 220 (Class 5)
Softening point (EN 1427)	≥ 35°C (Class 8)
Cohesion by pendulum (EN 13588)	NR

Stage 1 Durability - Stabilised Binder	
Durability of penetration @ 25°C (EN1426)	NPD
Durability of softening point (EN 1427)	NPD
Durability of cohesion by pendulum (EN 13588)	NPD
Stage 2 Durability - Aged Binder	
Durability of penetration @ 25°C (EN1426)	≤ 220 (Class 5)
Durability of softening point (EN 1427)	NPD
Durability of cohesion by pendulum (EN 13588)	≥ 1.0 J/cm <sup>2</sup> (Class 4)

Dangerous regulated substances	NPD
--------------------------------	-----

## SAFETY

For full safety information, please request the **Surfix 80S** Safety Data Sheet 15 using the contact information at the back of this brochure.





**SLX 80** is a BBA HAPAS approved premium grade polymer modified cationic bitumen emulsion. By using selected emulsifying agents with a suitable emulsion grade penetration bitumen it has been specifically designed for use as a hot applied surface dressing binder.

Conventional non-modified surface dressing binders may lack the cohesive strength necessary to retain chippings under the extra shear stress imposed on road surfaces by vehicles braking or turning sharply. The addition of polymer gives improved properties and enhanced performance. To aid application **SLX 80** has a slight thixotropic nature and excellent breaking properties.

## WHERE TO USE?

**SLX 80** is suitable for use on higher stressed, heavier trafficked sites as a premium grade surface dressing binder as specified in Road Note 39.

## PREPARATION

Please refer to the Road Surface Treatment Association's (RSTA)/ADEPT Code of Practice for Surface Dressing Part 5 - Surface Preparation.

## APPLICATION

**SLX 80** should be applied at a temperature of 85°C through a bulk binder distributor which has been tested for compliance to BS 1707 (hot binder distributors for surface dressing).

The surface dressing works should be in accordance with the recommendations contained in Design Guide for Road Surface Dressing, Road Note 39 and the RSTA's Codes of Practice for Surface Dressing.

Due to high residual binder viscosity, optimum results are obtained with **SLX 80** during the warmer months of May to August.

## COVERAGE

Refer to the Design Guide for Road Surface Dressing, Road Note 39 or contact our National Sales Office using the details at the back of this brochure for further guidance.

## PACKAGING

Supplied in bulk loads.

## STORAGE

**SLX 80** should be stored at 85°C in a purpose built bulk storage tank or spray tanker and circulated daily. For further information please refer to BS434-2 2006 Clause 5.2 Storage.

## STANDARDS

**SLX80** is a CE Marked cationic bitumen emulsion to BS EN13808:2013 C69BPF3/4 or C70BPF3/4.

**SLX80** complies with the requirements of Road Note 39, Design Guide for Road Surface Dressing as a Premium Grade surface dressing binder.

Full CE Marking information is available from the Colas Products website.  
[www.colasproducts.co.uk](http://www.colasproducts.co.uk)

Emulsion	
Binder content (EN 1428)	67 - 71% (Class 9) or ≥ 71 (Class 10)
Efflux 4mm @ 40°C (EN 12846-1)	5 - 100 s (Class 5/6)
Water effect on binder adhesion (EN 13614)	≥ 90 (Class 3)
Breaking behaviour (EN 13075-1)	70 - 195 (Class 3/4)

Recovered Binder	
Penetration @ 25°C (EN1426)	≤ 220 (Class 5)
Softening point (EN 1427)	≥ 43°C (Class 6)
Cohesion by pendulum (EN 13588)	≥ 1.2 J/cm <sup>2</sup> (Class 3)

Stage 1 Durability - Stabilised Binder	
Durability of penetration @ 25°C (EN1426)	NPD
Durability of softening point (EN 1427)	NPD
Durability of cohesion by pendulum (EN 13588)	NPD
Stage 2 Durability - Aged Binder	
Durability of penetration @ 25°C (EN1426)	NPD
Durability of softening point (EN 1427)	NPD
Durability of cohesion by pendulum (EN 13588)	NPD

## SAFETY

For full safety information, please request the **SLX 80** Safety Data Sheet 15 using the contact information at the back of this brochure.





# PREMIUM 80

# PREMIUM 80



**Premium 80** is a BBA HAPAS approved premium grade polymer modified cationic bitumen emulsion. By using selected emulsifying agents with a suitable emulsion grade penetration bitumen it has been specifically designed for use as a hot applied surface dressing binder.

## WHERE TO USE?

**Premium 80** is suitable for use on higher stressed, heavier trafficked sites as a premium grade surface dressing binder as specified in the Design Guide for Road Surface Dressing, Road Note 39.

## PREPARATION

Please refer to the Road Surface Treatment Association's (RSTA)/ADEPT Code of Practice for Surface Dressing Part 5 – Surface Preparation.

## APPLICATION

**Premium 80** should be applied at a temperature of 85°C through a bulk binder distributor which has been tested for compliance to BS 1707 (hot binder distributors for surface dressing).

The surface dressing works should be in accordance with the recommendations contained in Design Guide for Road Surface Dressing, Road Note 39 and the RSTA's Codes of Practice for Surface Dressing.

Due to high residual binder viscosity, optimum results are obtained with **Premium 80** during the warmer months of May to August.

## COVERAGE

Refer to the Design Guide for Road Surface Dressing, Road Note 39 or contact our National Sales Office using the details at the back of this brochure for further guidance.

## PACKAGING

Supplied in bulk loads.

## STORAGE

**Premium 80** should be stored at 85°C in a purpose built bulk storage tank or spray tanker and circulated daily. For further information please refer to BS434-2 2006 Clause 5.2 Storage.

## STANDARDS

**Premium 80** is a CE Marked cationic bitumen emulsion to BS EN13808:2013 C70BPF2/3/4.

**Premium 80** complies with the requirements of Road Note 39, Design Guide for Road Surface Dressing as a Premium Grade surface dressing binder.

Full CE Marking information is available from the Colas Products website.

[www.colasproducts.co.uk](http://www.colasproducts.co.uk)

Emulsion	
Efflux 4mm @ 40°C (EN 12846-1)	5 – 70 s (Class 5)
Water effect on binder adhesion (EN 13614)	≥ 90 (Class 3)
Breaking behaviour (EN 13075-1)	< 110 – 195 (Class 2/3/4)
Recovered Binders	
Penetration @ 25°C (EN 1426)	≤ 220 (Class 5)
Softening point (EN 1427)	≥ 46°C (Class 5)
Cohesion by pendulum (EN 13588)	≥ 1.2 J/cm <sup>2</sup> (Class 3)

### Stage 1 Durability - Stabilised Binder

Durability of penetration @ 25°C (EN1426)	NPD
Durability of softening point (EN 1427)	NPD
Durability of cohesion by pendulum (EN 13588)	NPD
Stage 2 Durability - Aged Binder	
Durability of penetration @ 25°C (EN1426)	NPD
Durability of softening point (EN 1427)	NPD
Durability of cohesion by pendulum (EN 13588)	NPD

Dangerous regulated substances	NPD
--------------------------------	-----

## SAFETY

For full safety information, please request the **Premium 80** Safety Data Sheet 16 using the contact information at the back of this brochure.



# PRINMULS MP90X

# PRINMULS MP90X



**Prinmuls MP90X** is a BBA HAPAS approved super premium grade polymer modified bitumen emulsion with a high binder content. Specifically designed for use as a heavy duty surface dressing binder on high speed and heavily trafficked roads.

## WHERE TO USE?

**Prinmuls MP90X** is suitable for use on higher stressed, heavier trafficked sites as a super-premium grade surface dressing binder as specified in the Design Guide for Road Surface Dressing, Road Note 39.

## PREPARATION

Please refer to the Road Surface Treatment Association's (RSTA)/ADEPT Code of Practice for Surface Dressing Part 5 – Surface Preparation.

## APPLICATION

**Prinmuls MP90X** should be applied at a temperature of 85°C through a bulk binder distributor which has been tested for compliance to BS 1707 (hot binder distributors for surface dressing).

The surface dressing works should be in accordance with the recommendations contained in Design Guide for Road Surface Dressing, Road Note 39 and the RSTA's Codes of Practice for Surface Dressing.

Due to high residual binder viscosity, optimum results are obtained with **Prinmuls MP90X** during the warmer months of May to August.

## COVERAGE

Refer to the Design Guide for Road Surface Dressing, Road Note 39 or contact our National Sales Office using the details at the back of this brochure for further guidance.

## PACKAGING

Supplied in bulk loads.

## STORAGE

**Prinmuls MP90X** should be stored at 85°C in a purpose built bulk storage tank or spray tanker and circulated daily. For further information please refer to BS434-2 2006 Clause 5.2 Storage.

## STANDARDS

**Prinmuls MP90X** is a CE Marked cationic bitumen emulsion to BS EN13808:2013 C70BPF2/3/4.

**Prinmuls MP90X** complies with the requirements of Road Note 39, Design Guide for Road Surface Dressing as a Super Premium Grade surface dressing binder.

Full CE Marking information is available from the Colas Products website.  
[www.colasproducts.co.uk](http://www.colasproducts.co.uk)

Emulsion	
Binder content (EN1428)	≥ 69 (Class 10)
Efflux 4mm @ 40°C (EN 12846-1)	5 - 100 s (Class 5/6)
Water effect on binder adhesion (EN 13614)	≥ 90 (Class 3)
Breaking behaviour (EN 13075-1)	70 - 195 (Class 3/4)
Recovered Binder	
Penetration @ 25°C (EN1426)	≤ 220 (Class 5)
Softening point (EN 1427)	≥ 50°C (Class 4)
Cohesion by pendulum (EN 13588)	≥ 1.4 J/cm <sup>2</sup> (Class 2)

Stage 1 Durability - Stabilised Binder	
Durability of penetration @ 25°C (EN1426)	NPD
Durability of softening point (EN 1427)	NPD
Durability of cohesion by pendulum (EN 13588)	NPD
Stage 2 Durability - Aged Binder	
Durability of penetration @ 25°C (EN1426)	≤ 150 (Class 5)
Durability of softening point (EN 1427)	NPD
Durability of cohesion by pendulum (EN 13588)	≥ 1.4 J/cm <sup>2</sup> (Class 2)

Dangerous regulated substances	NPD
--------------------------------	-----

## SAFETY

For full safety information, please request the **Prinmuls MP90X** Safety Data Sheet **16** using the contact information at the back of this brochure.





## BOND COATS

Colbond 50	70
Colbond Multi	72
Leotak	74



**Colbond 50** is nominally a 50% binder content polymer modified bitumen emulsion. **Colbond 50** forms a uniform film of polymer modified bitumen on the road surface which promotes a strong adhesive bond between a bituminous overlay and the existing surface. The application of **Colbond 50** also improves the waterproofing of the road pavement.

**Colbond 50**, when fully broken, prevents 'pick-up' on the wheels, tracks or tyres of the paver/delivery vehicles and prevents debonding of the overlay during subsequent service life when subjected to traffic stresses.

## WHERE TO USE?

- Carriageways
- Footways
- Car parks

## PREPARATION

Surface to be sprayed must be free from detritus, standing water, loose material and oil spillage.

## APPLICATION

Prior to the application **Colbond 50** should be circulated thoroughly. **Colbond 50** should be applied at 0.7l/m<sup>2</sup> to achieve the recommended 0.35kg/m<sup>2</sup> residual spread rate stated in BS594987: Clause 5.5.2.

Vehicular traffic should be kept off the treated area until the emulsion has fully broken and the colour changes from brown to black, then the overlay should be applied.

It is recommended that **Colbond 50** is only applied when the ground temperature is 5°C and rising or <40°C. Humidity should preferably not exceed 70% however **Colbond 50** can be applied in higher humidity but this will prolong the break time. Because the base binder used in **Colbond 50** is polymer modified, it behaves differently from conventional bitumen emulsions and it may therefore be necessary to warm the **Colbond 50** to ease application.

When applying through small motorised or petrol driven units ensure the sprayer system is flushed regularly, this is of particular importance when impeller driven pumps are used.

## COVERAGE

It is recommended that the **Colbond 50** is applied at coverage rates specified in BS594987 Clause 5.5 application of bond coats. For further information or guidance please contact our National Sales Office using the details at the back of this brochure.

## PACKAGING

**Colbond 50** is available in bulk or 200kg drums.

## STORAGE

Protect from frost. Bulk storage tanks should be circulated before use and maintained between 65-85°C. Drums should be rolled frequently to avoid separation. For further information please refer to BS434-2:2006 Clause 5.2 Storage.

## STANDARDS

**Colbond 50** is a CE Marked cationic emulsion to BS EN13808:2013 C50BP5 which also complies with BS594987 Clause 5.5 Application of bond coats.

Full CE Marking information is available from the Colas Products website.

[www.colasproducts.co.uk](http://www.colasproducts.co.uk)

Emulsion	
Binder content (EN 1428)	48-52% (Class 4)
Viscosity (EN 12846-1)	15 - 70 s (Class 3)
Breaking behaviour (EN 13075-1)	> 170 (Class 5)
Recovered binder minimum peak vialit cohesion (EN 13588)	> 1.0 J/cm <sup>2</sup> (Class 4)

## SAFETY

For full safety information, please request the **Colbond 50** Safety Data Sheet T1 using the contact information at the back of this brochure.

# COLBOND MULTI



**Colbond Multi** is a polymer modified cationic bitumen emulsion designed to be applied both as a bond coat and vertical joint paint. **Colbond Multi** forms a uniform film of polymer modified bitumen on both horizontal and vertical faces forming a strong adhesive bond between bituminous overlay and the existing surface.

In addition the application of **Colbond Multi** also improves the waterproofing of the road pavement. **Colbond Multi**, when fully broken, prevents 'pick-up' on the wheels, tracks or tyres of the paver/delivery vehicles and prevents disbanding/debonding of the overlay during subsequent service life when subjected to traffic stresses.

Applied to vertical edges **Colbond Multi** replaces conventional hot pour bitumen.

## WHERE TO USE?

- Carriageways
- Footways
- Car parks

## PREPARATION

Surface to be treated must be free from detritus, standing water, loose materials and oil spillage.

## APPLICATION

Prior to application **Colbond Multi** should be circulated thoroughly. **Colbond Multi** should be applied at 0.52l/m<sup>2</sup> to achieve the recommended 0.35kg/m<sup>2</sup> residual spread rate stated in BS594987: Clause 5.5 application of bond coats and 6.8 Joints.

Vehicular traffic should be kept off the treated area until the emulsion has fully broken, colour changes from brown to black, then the overlay should be applied.

It is recommended that **Colbond Multi** is applied when the ground temperature is 5°C and rising or <40°C. Humidity should preferably not exceed 70% however **Colbond Multi** can be applied in higher humidity but this will prolong the break time. **Colbond Multi** should be applied at 85°C using a mechanical spray tanker calibrated to BS1707 (Hot binder distributors for road surface dressing).

## COVERAGE

It is recommended that the **Colbond Multi** is applied at coverage rates specified in BS594987 Clause 5.5 Application of bond coats and 6.8 Joints. For further information or guidance please contact our National Sales Office using the details at the back of this brochure.

## PACKAGING

**Colbond Multi** is available in bulk loads.

## STORAGE

Protect from frost. Bulk material should be circulated before use. For further information please refer to BS434-2 2006 Clause 5.2 Storage.

## STANDARDS

**Colbond Multi** is a CE Marked cationic emulsion to BS EN13808:2013 C65BP4 or C67BP4.

Full CE Marking information is available from the Colas Products website.

[www.colasproducts.co.uk](http://www.colasproducts.co.uk)

# COLBOND MULTI

Emulsion	
Binder content (EN 1428)	65-69% (Class 8) 67-71% (Class 8)
Viscosity (EN 12846-1)	15 - 70 s (Class 3)
Breaking behaviour (EN 13075-1)	> 170 (Class 5)
Recovered binder minimum peak vialit cohesion (EN 13588)	> 1.0 J/cm <sup>2</sup> (Class 4)

## SAFETY

For full safety information, please request the **Colbond Multi** Safety Data Sheet 11 using the contact information at the back of this brochure.

# LEOTAK



**Leotak** is a cold applied rapid-acting 40% cationic bitumen emulsion. When cured **Leotak** forms a thin uniform film of bitumen on the road surface which gives an adhesive bond between a bituminous overlay and an existing surface. For best results, tack coating is strongly recommended when performing such tasks as overlaying with hot rolled asphalt, macadam or when patching or carrying out inlaid work.

**Leotak** adheres exceptionally well, even in damp conditions. The overlay is held securely in place and the entry of water between road pavement courses is hindered.

## WHERE TO USE?

- Carriageways
- Footways
- Car parks

## PREPARATION

Surface to be treated must be free from detritus, standing water, loose materials and oil spillage.

## APPLICATION

**Leotak** should be sprayed or hand applied between 0.3-0.6 l/m<sup>2</sup> (depending on the texture, porosity etc. of the surface) to give the thinnest film consistent with complete coverage.

Vehicular traffic should be kept off the treated area until the emulsion has fully broken, colour changes from brown to black. When emulsion has fully broken then apply the overlay.

## COVERAGE

1 x 25kg container should cover approximately 40m<sup>2</sup>

1 x 200kg drum should cover approximately 320m<sup>2</sup>

## PACKAGING

**Leotak** is available in bulk, 200kg drums, 25kg and 12.5kg containers.

## STORAGE

Protect from frost. Bulk material should be circulated before use. Drums should be rolled frequently to avoid separation. For further information please refer to BS434-2 2006 Clause 5.2 Storage.

## STANDARDS

**Leotak** is a CE Marked cationic emulsion to BS EN13808:2013 C40B.

**Leotak** also complies with the withdrawn BS434-1 Standard as a K1-40 Type emulsion.

Full CE Marking information is available from the Colas Products website.

[www.colasproducts.co.uk](http://www.colasproducts.co.uk)

## SAFETY

For full safety information, please request the **Leotak** Safety Data Sheet 23 using the contact information at the back of this brochure.



# MORTARS

Colas C45	76
Colas C60	78
Colas Cubeset	80
Colas HSC10	82

**Colas C45** is a pre-mixed cement based non-shrink bedding mortar suitable for the support of road ironwork and highway furniture.

When placed the mixed mortar will harden in approximately 10 minutes. The compressive strength gain will reach 20N/mm<sup>2</sup> within 45 minutes allowing early opening of roads to vehicular traffic. The self-contained product only needs to be mixed with water on site and the rapid setting assists the re-bedding of manhole frames and the setting of new frame systems.

The product is chloride free and can be safely used with cast iron and steel units.

## WHERE TO USE?

- Re-bedding of raised manhole frames
- Bedding of frames in new roads
- Support of road furniture

## PREPARATION

Laitance and all loose material including dust, oil and grease should be removed in order to produce a sound substrate. The work area should be pre-wetted taking care to remove any standing water before placing the **Colas C45** mortar.

Excess water should not be added once setting of the mortar has commenced and further mixing should not be used to re-work the mix.

The mortar should be placed within approximately 10 minutes of mixing. The working time may be extended in cold conditions and may be slightly shortened in hot conditions.

## APPLICATION

To achieve the most consistent mortar mix, mechanical mixing is recommended. Thorough hand mixing is suitable but care should be taken to ensure that the mix is fully wetted out without the use of excess water. Mechanical mixing may be carried out in a suitable vessel using a slow speed high torque drill and Mortar Stirrer. Hand mixing may be carried out using a clean spot board or wheelbarrow. Each 25kg bag of **Colas C45** requires to be mixed with 3.3 litres of water to give a mortar consistency.

Set suitable levelling shims onto the working surface ready to receive the frame or unit.

Place the mixed mortar onto the prepared surface and lower the frame or unit onto the mortar and knock down onto the pre-set shims to line and level. The bed thickness laid in a single application should be between 15-75mm. Thicker support beds can be achieved by applying further material as soon as the lower bed has hardened sufficiently not to damage the original bed.

The placed mortar will have hardened sufficiently to carry out further work, such as haunching, within 20 minutes depending on the ambient conditions. Alternatively thicker beds may be formed by adding clean dry pea shingle up to a maximum of 30% of the weight of the **Colas C45**. No additional water is required for mixing.

Curing: No special curing is required at temperatures between 5°C and 35°C. For placing at temperatures outside this range, contact our National Sales Office.

## COVERAGE

Each 25kg bag of **Colas C45** will enable a manhole frame 600mm x 600mm to be raised approximately 25mm.

The volume yield of each 25kg bag of **Colas C45** is approximately 12.75 litres.

## PACKAGING

**Colas C45** is supplied in 25kg sack bags (50 x 25kg bags per pallet) and 25kg buckets (40 x 25kg per pallet).

## STORAGE

**Colas C45** will have a shelf life of 6 months when kept in dry conditions at a temperature of 5°C to 35°C.

## STANDARDS

**Colas C45** has been tested in accordance with appropriate parts of EN 12390. The product conforms to DTp: HD 27/15. Design Manual for Roads and Bridges V7 Sec2 3.11. Mortars for bedding ironwork such as manhole cover frames during repairs may be trafficked when the strength has reached 20N/mm<sup>2</sup>. For rapid construction, this strength should be achieved within 2 hours. **Colas C45** will achieve the required strength of 20N/mm<sup>2</sup> within 45 minutes at a temperature of 20°C.

## PERFORMANCE

Compressive Strength (Water addition: 2.75 litres per 25kg of **Colas C45**).

Typical Mortar Properties @ 20°C		
Compressive strength	45 mins	20MPa
	60 mins	25MPa
	1 day	35MPa
	7 days	45MPa
	28 days	55MPa
Density	2,200 kg/m <sup>3</sup>	
Approx. working life @ 20°C	10 mins	

Variations in water content and ambient temperature for particular applications may alter mortar consistency and compressive strength achieved.

## SAFETY

For full safety information, please request the **Colas 45** Safety Data Sheet 119 using the contact information at the back of this brochure.

**Colas C60** is a pre-mixed cement based non-shrink bedding mortar suitable for the support of road ironwork and highway furniture.

The mixed mortar, when laid, will harden in approximately 10 minutes. The compressive strength gain will reach 20N/mm<sup>2</sup> within 1 hour allowing early opening of roads to vehicular traffic. The self-contained product only needs to be mixed with water on site and the rapid setting assists the re-bedding of manhole frames and the setting of new frame systems.

The product is chloride free and can be safely used with cast iron and steel units.

## WHERE TO USE?

- Re-bedding of raised manhole frames
- Bedding of frames in new roads
- Support of road furniture

## PREPARATION

Laitance and all loose material including dust, oil and grease should be removed in order to produce a sound substrate. The work area should be rewetted taking care to remove any standing water before placing the **Colas C60** mortar.

Excess water should not be added once setting of the mortar has commenced, further mixing should not be used to re-work the mix. The mortar should be placed within approximately 10 minutes of mixing. The working time may be extended in cold ambient conditions and may be slightly shortened in hot ambient conditions.

## APPLICATION

To achieve the most consistent mortar mix, mechanical mixing is recommended. Thorough hand mixing is suitable but care should be taken to ensure that the mix is fully wetted out without the use of excess water. Mechanical mixing may be carried out in a suitable vessel using a slow speed high torque drill and Mortar Stirrer. Hand mixing may be carried out using a clean spot board or wheelbarrow. Each 25kg bag of **Colas C60** requires to be mixed with 3.3 litres of water to give a mortar consistency.

Set suitable levelling shims onto the working surface ready to receive the frame or unit. Place the mixed mortar onto the prepared surface and lower the frame or unit onto the mortar and knock down onto the pre-set shims to line and level. The bed thickness applied in a

single application should be between 15-75mm. Thicker support beds can be achieved by applying further material as soon as the lower bed has hardened sufficiently not to damage the original bed.

The placed mortar will have hardened sufficiently to carry out further work, such as haunching, within 20 minutes depending on the surrounding ambient conditions. Alternatively thicker beds may be formed by adding clean dry pea shingle up to a maximum of 30% of the weight of the **Colas C60**. No additional water is required for mixing. After placement no special curing is required in moderate ambient conditions.

The placed mortar will have hardened sufficiently to carry out further work, such as haunching, within 20 minutes depending on the surrounding ambient conditions.

Curing: No special curing is required at temperatures between 5°C and 35°C. For placing at temperatures outside this range, contact our National Sales Office.

## COVERAGE

Each 25kg bag of **Colas C60** will enable a manhole frame 600mm x 600mm to be raised approximately 25mm.

The volume yield of each 25kg bag of **Colas C60** is approximately 12.75 litres.

## PACKAGING

**Colas C60** is supplied in 25kg sack bags (50 x 25kg bags per pallet) and 25kg buckets (40 x 25kg per pallet).

## STORAGE

**Colas C60** will have a shelf life of 6 months when kept in dry conditions at a temperature of 5°C to 35°C.

## STANDARDS

**Colas C60** has been tested in accordance with appropriate parts of EN 12390. The product conforms to DTp: HD 27/15. Design Manual for Roads and Bridges V7 Sec 2 3.11 Mortars for bedding ironwork such as manhole cover frames during repairs may be trafficked when the strength has reached 20N/mm<sup>2</sup>. For rapid construction, this strength should be achieved within 2 hours. **Colas C60** will achieve the required strength of 20N/mm<sup>2</sup> within 1 hour at a temperature of 20°C.

## PERFORMANCE

Typical Mortar Properties @ 20°C		
Compressive strength	60 mins	20MPa
	1 day	35MPa
	7 days	45MPa
	28 days	55MPa
Density	2,200 kg/m <sup>3</sup>	
Approx. working life @ 20°C	10 mins	

Variations in water content and ambient temperature for particular applications may alter mortar consistency and compressive strength achieved.

## SAFETY

For full safety information, please request the **Colas C60** Safety Data Sheet 120 using the contact information at the back of this brochure.



**Colas Cubeset** is a single pre-mixed cement based non-shrink concrete designed with selected graded silica aggregates and additives. The mixed product may be placed in sections of 20mm up to 650mm in a single pour.

**Colas Cubeset** is suitable for all concrete works where early strength development is required in order to allow early use of the placed sections. The product may be used for localised repairs plus large area placement or re-instatement of concrete pavements.

The mixed concrete, when placed, will harden in approximately 20 minutes. The compressive strength gain will reach 22N/mm<sup>2</sup> within 2 hours allowing early opening of sections to foot and vehicular traffic. The self-contained product only needs to be mixed with water on site.

The product is chloride free and can be safely used in contact with steel reinforcement. After placement no special curing is required in moderate ambient conditions. In rapid drying conditions, expected rain or frost protection should be applied.

## WHERE TO USE?

- Concrete restoration - recasting with concrete or mortar
- Structural strengthening - adding mortar or concrete
- Increasing physical resistance - adding mortar or concrete
- Resistance to chemicals - adding mortar or concrete
- Preserving or restoring passivity - increasing cover with additional mortar or concrete
- Preserving or restoring passivity - replacing contaminated or carbonated concrete

Other uses include:

- Concrete repairs to accept foot and vehicular traffic
- Forming of new pavement areas
- Re-instatement of deteriorated pavement areas
- Rapid repairs to roadways & runways
- Structural support situations

## PREPARATION

Laitance and all loose material including dust, oil and grease should be removed in order to produce a sound substrate. The work area should be pre-wetted taking care to remove any standing water before placing the **Colas Cubeset**.

Excess water should not be added. Once setting of the concrete has commenced, further mixing should not be used to re-work the mix. The concrete should be placed within approximately 15 minutes of mixing. The working time may be extended in cold ambient conditions and may be slightly shortened in hot ambient conditions. For cold weather working warm mixing water at up to 30°C may be used.

## APPLICATION

To achieve the most consistent concrete mix, mechanical mixing using a forced action mixer such as the Creteangle is recommended. Small mixes may be made using a heavy duty slow speed high torque drill and Mortar Stirrer. Each 25kg bag of **Colas Cubeset** requires 2.25 litres of water to give a medium workability concrete consistency. Part bag mixing should not be undertaken.

Mixed **Colas Cubeset** should be placed onto the dampened prepared surface as soon as mixing is complete. Once placed fully compact the concrete to obtain maximum strength development. The bed thickness applied in a single application should be between 20-650mm. The placed concrete will have hardened sufficiently to carry out further work within 20 minutes depending on the surrounding ambient conditions.

Curing: No special curing is required at temperatures between 5°C and 35°C. For placing at temperatures outside this range, contact our National Sales Office.

At early stages do not allow placed concrete to rapidly dry and protect from rain and frost.

## COVERAGE

The volume yield of each 25kg bag of **Colas Cubeset** is approximately 11.5 litres.

## PACKAGING

**Colas Cubeset** is supplied in 25kg sack bags (50 x 25kg per pallet).

## STORAGE

**Colas Cubeset** will have a shelf life of 6 months when kept in dry conditions at a temperature of 5°C to 35°C. Storage at higher temperatures or high humidity may reduce the shelf life.

## STANDARDS

**Colas Cubeset** has been tested in accordance with appropriate parts of EN12390, EN13412.

**Colas Cubeset** meets the requirements of the Highways England Specification for Highway Works Series 1700 for Structural Concrete.

## PERFORMANCE

Typical Mortar Properties @ 20°C		
Compressive strength	120 mins	20MPa
	1 day	35MPa
	7 days	45MPa
	28 days	65MPa
Density	2,200 - 2,300 kg/m <sup>3</sup>	
Approx. working life @ 20°C	15 mins	
Elastic modulus in compression	41.2GPa @ 28 days	
Bond strength via pull off test	2.4MPa @ 28 days	
Cl Content	<0.003%	

Variations in water content and ambient temperature for particular applications may alter mortar consistency and compressive strength achieved.

## SAFETY

For full safety information, please request the **Colas Cubeset** Safety Data Sheet 122 using the contact information at the back of this brochure.

**Colas HSC10** is a pre-packaged cement based concrete containing graded aggregates and non-shrink additives. **Colas HSC10** is supplied to site ready to use only requiring the addition of mixing water to produce a medium workability high strength durable concrete.

The mixed concrete, when placed, will harden in approximately 10 minutes and reach initial set in approximately 15 minutes. **Colas HSC10** can be placed in a single pass from 30mm to 400mm. Thicker sections can be achieved by placing additional layers once the preceding layer has reached initial set. The compressive strength gain will reach 18N/mm<sup>2</sup> within 1 hour allowing early opening of roads to vehicular traffic.

The rapid setting assists the re-bedding of manhole frames and the setting of new frame systems. The product is chloride free and can be safely used with cast iron and steel units. After placement, no special curing is required in moderate ambient conditions.

## WHERE TO USE?

- Infilling around re-bedded raised manhole
- Infilling around manhole frames in new roads
- Support of road furniture

## PREPARATION

Laitance and all loose material including dust, oil and grease should be removed in order to produce a sound substrate. The work area should be pre-wetted taking care to remove any standing water before placing the **Colas HSC10** concrete.

## APPLICATION

To achieve the most consistent concrete mix, mechanical mixing is recommended. Thorough hand mixing is suitable but care should be taken to ensure that the mix is fully wetted out without the use of excess water. Mechanical mixing may be carried out in a suitable vessel using a slow speed high torque drill and paddle. Hand mixing may be carried out using a clean spot board or wheelbarrow.

Each 25kg tub or bag of **Colas HSC10** requires 1.0 to 1.75 litres of water to give a stiff concrete. Excess water should not be added. Combine the aggregate and cement portions and gradually add water until a stiff concrete consistency is achieved. Once setting of the concrete has commenced, further

mixing should not be used to re-work the mix. The concrete should be placed within approximately 5 minutes of mixing. The working time may be extended in cold ambient conditions and may be slightly shortened in hot ambient conditions.

Required mixing water is 1.0 to 1.75 litres. Aggregates as supplied contain moisture. Do not add excessive water. Variations in water content for particular applications may alter concrete consistency and compressive strength achieved. Place mixed concrete onto dampened prepared substrate as soon as possible after mixing. Compact concrete into place using a suitable tamp or float. Tools and mixers should be cleaned with water before the **Colas HSC10** has hardened.

Curing: No special curing is required at temperatures between 5°C and 35°C. For placing at temperatures outside this range, contact our National Sales Office.

## COVERAGE

The volume yield of each 25kg bag of **Colas HSC10** is approximately 12 litres.

## PACKAGING

**Colas HSC10** is supplied in 25kg bags (50 x 25kg bags per pallet) and 25kg buckets (40 x 25kg per pallet).

## STORAGE

**Colas HSC10** will have a shelf life of 6 months when kept in unopened packaging at a temperature of 5°C to 35°C. Storage at higher temperatures may reduce the shelf life.

## STANDARDS

**Colas HSC10** is manufactured in accordance to BS EN ISO 9001:2015.


## PERFORMANCE

Typical Mortar Properties @ 20°C		
Compressive strength	60 mins	18MPa
	1 day	40MPa
	28 days	60MPa
Particle size	0 - 10.0 mm	
Density	2,300 - 2,400 kg/m <sup>3</sup>	
Approx. working life @ 20°C	10 mins	

Concrete for installing ironwork such as manhole cover frames during repairs may be trafficked when the strength is expected to be 20N/mm<sup>2</sup>. For rapid construction, this strength should be achieved within 2 hours. **Colas HSC10** will achieve the required strength of 20N/mm<sup>2</sup> within 1½ hours at a temperature of 20°C.

## SAFETY

For full safety information, please request the **Colas HSC10** Safety Data Sheets 154 & 155 using the contact information at the back of this brochure.



# ANCILLIARY PRODUCTS

Leoseal R	86
TPF Masterbatch	88
CP Primer	89
Leoclean Industrial	90
Leoclean Standard	91
Oxidised Bitumen	92
Pre-Coated Chippings	93

# LEOSEAL R



**Leoseal R** is an economical flexible waterproofer and crack sealant designed for easy hand application.

**Leoseal R** is a specially formulated combination of bitumen emulsion modified with an elastomer which together form a tough and long-lasting barrier against the entry of water.

**Leoseal R** has excellent adhesive properties and can be applied to green concrete or damp surfaces.

## WHERE TO USE?

- Waterproofing below ground concrete structures
- Crack sealant for roads and footways

## PREPARATION

Work should not be carried out in wet or frosty weather.

Surfaces must be dry or damp (no standing or running water), as well as clean and free from dust, oil and fuel spillage.

## APPLICATION

Stir contents of the bucket prior to use.

### WATERPROOFING

Apply **Leoseal R** in two coats using a turks head brush. The first coat should be at a rate of 0.55l/m<sup>2</sup> with the second applied at right angles at a rate of 0.45l/m<sup>2</sup>. If the surface is hot, very dry or absorbent it may be helpful to first prime the surface with a thin coat of **Leoseal R** diluted in a ratio of 1 part water to 8 parts **Leoseal R**.

When finished, wash brushes with **Leoclean** immediately followed by soapy water.

When backfilling is necessary the **Leoseal R** treatment should not be left longer than 3-4 weeks before this is undertaken.

### CRACK SEALING

#### Cracks up to 3mm.

Pour **Leoseal R** into the crack using a spouted can.

Any surplus on the surface should be brushed or squeegeed out to a thin film and dusted over after drying with cement or very fine sand to remove the tack.

#### Cracks >3mm and up to 25mm

Prime the sides of the crack with a brush coat of **Leoseal R**.

Mix **Leoseal R** with damp sand in the ratio of 1:1 by volume to produce a mortar.

Fill crack with the mortar mix.

Compact the material into the crack and smooth off the surface with a trowel.

N.B: **Leoseal R** sets by the evaporation of water from the product. Application should only be carried out in good drying conditions. A rain resistant set will be delayed if the weather is cold, damp or humid.



## COVERAGE

Waterproofing: 1l/m<sup>2</sup>

Crack Sealing: this cannot be quantified as it depends on the depth of the crack.

## PACKAGING

**Leoseal R** is supplied in 200kg drums or 15kg re-sealable plastic buckets.

## STORAGE

Protect from frost.

## STANDARDS

**Leoseal R** is a proprietary product manufactured to ISO9001 quality system which covers all Colas manufactured products

## SAFETY

For full safety information, please request the **Leoseal R** Safety Data Sheet 10 using the contact information at the back of this brochure.

# LEOSEAL R

# TPF MASTERBATCH



**TPF Masterbatch** is a fluxing agent developed to enable more flexibility in the manufacture of a storage macadam.

## WHERE TO USE?

**TPF Masterbatch** is used for the manufacture of deferred set macadam.

## APPLICATION

Why use **TPF Masterbatch**

- No evolution of diluents in storage ensuring consistency of viscosity
- No heating costs during storage
- Storage temperature is approximately 80°C below flashpoint
- Ability to compensate for dense mixes and seasonal changes and varying storage temperature requirements in order to optimise costs
- Uses normal plant bitumens

For further information please contact the National Sales Office.

## PACKAGING

Supplied in bulk or IBCs.

## STORAGE

Store at ambient temperature.

## STANDARDS

Flash point	>105°C (PMCC BS2000-34)
Storage/pumping temperature	Ambient
Recommended aggregate mixing temperature	70 - 105°C
Solubility in CH2 Cl2	100%wt
Density @ 15°C	0.86 - 0.875 g/ml

## PROPERTIES

**TPF Masterbatch** is a proprietary product manufactured to ISO9001 quality system which covers all Colas manufactured products.

## SAFETY

For full safety information, please request the **TPF Masterbatch** Safety Data Sheet 17 using the contact information at the back of this brochure.

# CP PRIMER



**CP Primer** is a high quality, low viscosity resin/rubber solution for priming surfaces prior to the application of **Colas Preformed Surface Dressing** and **Colasgrip**. It should also be used for the priming of joints prior to the application of **Colas Jointfill A2**, **Jointfill N1** and **Coljoint N2** sealant.

## WHERE TO USE?

See above.

## PREPARATION

Surfaces must be clean and free from dust, oil and fuel spillage.

## APPLICATION

**CP Primer** can be applied by either brush or roller to damp but not wet surfaces. It should be applied at ambient temperatures of between 2°C and 30°C.

### PREFORMED SURFACE DRESSING

Apply **CP Primer** as thinly and evenly as possible and allow to become touch dry before applying the **Preformed Surface Dressing**. Applying too much could result in the primer bleeding through or the de-bonding of the **Preformed Surface Dressing**.

### COLASGRIP

For concrete surfaces apply **CP Primer** as thinly and evenly as possible and allow to become touch dry before applying **Colasgrip**.

### JOINT SEALING

Allow the **CP Primer** to dry completely, allowing a minimum of 30 minutes on a dry surface or 90 minutes on a damp surface before applying sealant. Apply sealant within 6 hours. A spread rate of 0.1-0.2l/m<sup>2</sup> should be achieved depending on the porosity of the base. Cellulose thinners should be used to clean tools.

## COVERAGE

**CP Primer** should be applied as thinly and evenly as possible to achieve a coverage rate of 0.1-0.2l/m<sup>2</sup>.

## PACKAGING

**CP Primer** is available in 5 litre metal containers (4 per box).

## STORAGE

**CP Primer** has a 12 month storage life in original unopened containers. Protect from frost and direct sunlight.

## STANDARDS

**CP Primer** is produced to a manufacturing system accredited to ISO9001.

## SAFETY

For full safety information, please request the **CP Primer** Safety Data Sheet 05 using the contact information at the back of this brochure.

# LEOCLEAN INDUSTRIAL



**Leoclean Industrial** is a heavy duty cleaner designed to remove bitumen and asphalt grease from all types of equipment used by Highways Contractors. It has been formulated so that when applied it will leave a non-slip coating that will help prevent material from adhering to the surface of the equipment used.

**Leoclean Industrial** is a cleaner and degreaser, formulated from derivatives of vegetable oils with a flash point in excess of 90°C.

**Leoclean Industrial** can replace red diesel as well as chlorinated and paraffin based solvents in most applications.

## WHERE TO USE?

**Leoclean Industrial** is suitable for most surfaces. It is completely safe on all metals, most composite plastics, ceramics, most acrylics, concretes, brick, stone, glass, wood and painted surfaces. It will also not affect any cured resins or vulcanized rubber. Care must be taken on porous surfaces as **Leoclean Industrial** will tend to allow absorption of the contaminant into the surface.

## APPLICATION

**Leoclean Industrial** should be applied sparingly onto the affected area and allowed to soak into the contaminant. The softened or dissolved residue should then be removed with absorbent material. Repeat the process if necessary. Remove softened residue off porous surfaces as soon as possible to reduce the risk of any absorption and wash with soapy water. **Leoclean Industrial** has a slower evaporation rate than chlorinated solvent. Where production processes require speed, drying can be enhanced by heat and/or hot air (but not naked flames) and/or vacuum.

## COVERAGE

The concentrated nature of **Leoclean Industrial** means that it should be used sparingly.

## PACKAGING

**Leoclean Industrial** is available in 5 and 25 litre plastic containers as well as 200 litre drums.

## STORAGE

Store in original container wherever possible. Protect from direct sunlight. Do not spray on naked flame or any incandescent material. Keep out of reach of children.

## STANDARDS

**Leoclean Industrial** is manufactured on a purpose-built plant to an ISO 9001 quality system which covers all Colas manufactured products.

## SAFETY

For full safety information, please request the **Leoclean Standard/Industrial** Safety Data Sheet 75 using the contact information at the back of this brochure.

# LEOCLEAN STANDARD



## APPLICATION

Apply **Leoclean Standard** sparingly onto affected area, and allow it to soak into the contaminant. The softened or dissolved residue should then be removed with absorbent material. Repeat the process if necessary. Remove softened residue off porous surfaces as soon as possible to reduce absorption and wash with soapy water. Where production processes require speed, drying can be enhanced by heat and/or hot air (but not naked flames) and/or vacuum. **Leoclean Standard** should be washed from the skin using soap and water.

## COVERAGE

The concentrated nature of **Leoclean Standard** means that it should be used sparingly.

## PACKAGING

**Leoclean Standard** is available in 500ml trigger bottles, 5 litre and 25 litre plastic containers and, on request, 200kg drums.

## STORAGE

Store in original container wherever possible. Protect from direct sunlight. Do not spray on naked flame or any incandescent material. Keep out of reach of children.

## STANDARDS

**Leoclean Standard** is manufactured on a purpose-built plant to an ISO 9001 quality system which covers all Colas manufactured products.

## SAFETY

For full safety information, please request the **Leoclean Standard/Industrial** Safety Data Sheet 75 using the contact information at the back of this brochure.

**Leoclean Standard** is ideal as a heavy duty cleaner for removing mineral oil based marks such as bitumen, asphalt, grease and carbon. It will remove waxes, adhesives, uncured paint and varnish, and also oil based inks.

**Leoclean Standard** is a cleaner and degreaser, formulated from derivatives of vegetable oils with a flash point in excess of 90°C.

**Leoclean Standard** can replace red diesel as well as chlorinated and paraffin based solvents in most applications, thus offering a safer alternative for effective cleaning and degreasing.

## WHERE TO USE?

**Leoclean Standard** will help clean up creosote, chewing gum, sealants and other mastics. It is ideal for cleaning oil spills off hard surfaces, cleaning combustion engines, parts washing, tank cleaning and adhesive residue removal.

**Leoclean Standard** is suitable for most surfaces. It is completely safe on all metals, ceramics, concrete, brick, stone, glass, wood and painted surfaces. It will not affect any cured resins and is safe on most fabrics. However, care should be taken when using on silk, leather and some plastics, acrylics and rubbers. Vulcanised rubber is unaffected. On porous surfaces **Leoclean Standard** will tend to allow absorption of the contaminant into the surface.

# OXIDISED BITUMEN



**Oxidised Bitumen** is a hot applied bitumen complying with BS EN 13304.

## WHERE TO USE?

**Oxidised Bitumen** is approved for use as components for the manufacture of roofing, flooring, water-proofing, adhesive, sealing and anti-corrosion products.

## PREPARATION

Ensure area to be treated is clean and free from dust, fuel and oil spillage.

## APPLICATION

For best results use a heating kettle with an indirect heating system such as hot oil. Ensure that the heating temperature doesn't exceed 200°C and that the oil does not exceed 230°C. When hot, pour either from a melter pourer or galvanised bucket with a 'V' lip.

## COVERAGE

Varies depending on the application.

## PACKAGING

**Oxidised Bitumen** is available in 25kg silicone coated paper cylinders.

## STORAGE

**Oxidised Bitumen** should be kept under cover and away from direct sunlight.

## STANDARDS

**Oxidised Bitumen** comply with BS EN13304 (Bitumen and Bituminous Binders Framework for Specification of **Oxidised Bitumen's**).

## SAFETY

SAFETY HANDLING PRECAUTIONS (when hot)

- Wear suitable protective clothing (heat resistant gauntlet gloves, overalls, protective footwear, face visor)
- DO NOT allow water to contact hot material
- DO NOT exceed maximum safe heating temperature
- If molten material contacts skin:
  - DO NOT attempt to remove
  - Immerse affected area in cold running water for at least 10 minutes
  - Seek medical advice without delay

This product is hazardous for transportation when carried at temperatures above 100°C.

For full safety information, please request the **Oxidised Bitumen** Safety Data Sheet 12A using the contact information at the back of this brochure.

# PRE-COATED CHIPPINGS



**Pre-Coated Chippings** are rolled into hot rolled asphalt to form part of the surface. They are resistant to polishing and can be used as part of the laying process to achieve the desired skid resistance which is 65psv in all types of roads from motorways to housing estates. **Pre-Coated Chippings** let you reinstate even the smallest of hot rolled asphalt patches without having to buy the chippings by the tonne.

## WHERE TO USE?

- Utility reinstatements
- Hot roll asphalt road patching works
- New hot rolled asphalt surfaces

## PREPARATION

To be used in hot tolled asphalt application.

## APPLICATION

To be applied by hand or an asphalt hopper.

## COVERAGE

The mass of coated chippings required to achieve a given rate of spread is determined by the contractor.

## PACKAGING

**Pre-Coated Chippings** are available in tonne bags or 25kg bags.

## STORAGE

To be stored out of direct sunlight or extreme heat. Do not freeze.

## STANDARDS

**Pre-Coated Chipping** complies with BE EN 1308-4 2016 specifies requirements for mixtures of the mix group Hot Rolled Asphalt for use on roads, airfields and other trafficked areas.



**A RANGE OF TOOLS ARE  
ALSO AVAILABLE THROUGH  
OUR NETWORK OF DEPOTS**

Please contact your local depot for more information.



# CONTACT INFORMATION

## National Sales Office

Loushers Lane  
Warrington  
Cheshire  
WA4 6RZ  
T: 01925 632 616

## East Kilbride Depot

7 Glenfield Road  
East Kilbride  
G75 0RA  
T: 01355 241 242

## Newcastle Depot

c/o Gurteens Transport,  
Unit 21 Mylord Crescent,  
Camperdown  
Industrial Estate,  
Killingworth  
NE12 5UJQ  
T: 0191 414 7674

## York Depot

Unit 1, Birch Court  
Osballdwick Link Road  
Osballdwick  
York  
YO19 5JA  
T: 01904 431 787

## Birmingham Depot

Cakemore Road  
Rowley Regis  
Birmingham  
B65 0QU  
T: 0121 561 4332

## Rowfant Depot

Wallage Lane  
Rowfant  
Crawley  
West Sussex  
RH10 4NF  
T: 01342 711 184

## Exeter Depot

Tan Lane  
Exeter  
EX2 8EG  
T: 01392 207 201